

Received: 04/03/2001	Completed: 04/10/2001	Letter: K	rb	P.O.#:	Test Report #:	2-33913-0-
Client's Identification	Normandy: Polyester scrim fabric with PVC coating, used for front-lit sign/billboard application. It can be printed on. Color: White.					
Tested For: Brian Lynch	Ultraflex Systems Inc. 365 Franklin Avenue Rockaway, NJ 07866				Key Test: NFPA 701-96 TM#2 Flat MEA	275
			Tel: 1-(973)-627-8608		Ext:	
			Fax: 1-(973)-627-7022			

Test Category: NFPA 701-96 TM2      Specifier: NYC Flex Signs      CODE: 275-375-1675

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Resistant Textiles and Films 1996  
 Edition - Test Method #2 - Flat Sheet Specimens  
 as cited by The City of New York Department of Buildings Technical Policy and Procedure Notice #11/99 -  
 Safety Standards for the Erection of Flex Sign Structures

SPECIMEN CONFIGURATION:  Single Layer;  Multi Layer

TESTED:  Initially  
 After 72 hours water leaching  
 After 100 hours accelerated weathering

RESULTS: specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0.0	0.0	270
2	0.0	0.0	340
3	0.0	0.0	300
4	0.0	0.0	280
5	0.0	0.0	240
6	0.0	0.0	270
7	0.0	0.0	260
8	0.0	0.0	260
9	0.0	0.0	310
10	0.0	0.0	260

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 440 g/m<sup>2</sup>

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

TEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

Passes;  Fails;  Requires testing of 5 additional specimens

(continued on page 2)

Received: 04/03/2001	Completed: 04/10/2001	Letter: K	rb	P.O.#:	Test Report #:	2-33913-0-
Client's Identification:	Normandy: Polyester scrim fabric with PVC coating, used for front-lit sign/billboard application. It can be printed on. Color: White.					
Ordered For: <b>Brian Lynch</b>					Key Test: NFPA 701-96 TM#2 Flat MEA	275
Ultraflex Systems Inc. 365 Franklin Avenue Rockaway, NJ 07866				Tel: 1-(973)-627-8608		Ext:
				Fax: 1-(973)-627-7022		

CONVERSION FACTORS:    mm ÷ 25.4 = inches  
                                  g/m<sup>2</sup> ÷ 28.35 x .935 = oz/yd<sup>2</sup>

REMARKS:  
None.

CERTIFICATION:  
We certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 1996 Edition Test Method #2 Flat Sheet Specimens.

*Heather G. Robertson*  
\_\_\_\_\_  
AUTHORIZED SIGNATURE  
THE GOVMARK ORGANIZATION, INC.