The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received: 11/17/2005	Completed: 11/21/2005	Letter: A	her	P.O.#:	Test Report #: 2-60255-0-

Client's Identification: Lot No.: 10165. Date of Mfg.: 8/3/05. Style: Eclipse. Composition: PVC Coated polyester scrim fabric for signs. Weight: 13oz/440 g. Thickness: 38 mm. End Use: Banners & Signs.

Tested For: **Brenda Siemer**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: NFPA 701-96 TM#2 Flat MEA 285

Tel: 1-(973)-627-8608 **Ext:** 119
Fax: 1-(973)-627-8506

Test Category: NFPA 701-96 TM2 Specifier: NYC Flex Signs CODE: 285-435-1685

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Resistant Textiles and Films 1996 Edition - Test Method #2 - Flat Sheet Specimens
as cited by The City of New York Department of Buildings Technical Policy and Procedure Notice #11/99 - Safety Standards for the Erection of Flex Sign Structures

SPECIMEN CONFIGURATION: [x] Single Layer; [ ] Multi Layer

RESULTS REPORTED: [x] Initially
[ ] After 72 hours water leaching
[ ] After 100 hours accelerated weathering

RESULTS: Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	250
2	0	0	230
3	0	0	240
4	0	0	220
5	0	0	260
6	0	0	220
7	0	0	220
8	0	0	230
9	0	0	220
10	0	0	190

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 517 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

[x] Passes; [ ] Fails; [ ] Requires testing of 5 additional specimens

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received: 11/17/2005	Completed: 11/21/2005	Letter: A	her	P.O.#:	Test Report #: 2-60255-0-

Client's Identification Lot No.: 10165. Date of Mfg.: 8/3/05. Style: Eclipse. Composition: PVC Coated polyester scrim fabric for signs. Weight: 13oz/440 g. Thickness: 38 mm. End Use: Banners & Signs.

Tested For: **Brenda Siemer**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: NFPA 701-96 TM#2 Flat MEA 285

Tel: 1-(973)-627-8608 **Ext:** 119
Fax: 1-(973)-627-8506

PRECONDITIONING: [x] 1 hr @ 220°F (Standard)
[ ] 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

CONVERSION FACTORS: mm ÷ 25.4 = inches
g/m² ÷ 28.35 x .835 = oz/yd²

REMARKS:
None.

CERTIFICATION:
I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 1996 Edition Test Method #2 Flat Sheet Specimens.

Heather E. Robertson

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. /jd

MS. HEATHER ROBERTSON

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from The Govmark Organization, Inc.

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received: 11/17/2005	Completed: 11/22/2005	Letter: A1	her	P.O.#:	Test Report #: 2-60255-1-

Client's Identification Lot No.: 10165. Date of Mfg.: 8/3/05. Style: Eclipse. Composition: PVC Coated polyester scrim fabric for signs. Weight: 13oz/440 g. Thickness: 38 mm. End Use: Banners & Signs.

Tested For: **Brenda Siemer**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: NFPA 701-96 TM#2 Flat MEA WL 285

Tel: 1-(973)-627-8608 **Ext:** 119
Fax: 1-(973)-627-8506

Test Category: NFPA 701-96 TM2 Specifier: NYC Flex Signs CODE: 285-435-1685

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Resistant Textiles and Films 1996 Edition - Test Method #2 - Flat Sheet Specimens
as cited by The City of New York Department of Buildings Technical Policy and Procedure Notice #11/99 - Safety Standards for the Erection of Flex Sign Structures

SPECIMEN CONFIGURATION: [x] Single Layer; [ ] Multi Layer

RESULTS REPORTED: [ ] Initially
[x] After 72 hours water leaching
[ ] After 100 hours accelerated weathering

RESULTS: Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	200
2	0	0	170
3	0	0	190
4	0	0	190
5	0	0	190
6	0	0	210
7	0	0	160
8	0	0	150
9	0	0	170
10	0	0	180

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 517 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

[x] Passes; [ ] Fails; [ ] Requires testing of 5 additional specimens

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received: 11/17/2005	Completed: 11/22/2005	Letter: A1	her	P.O.#:	Test Report #: 2-60255-1-

Client's Identification Lot No.: 10165. Date of Mfg.: 8/3/05. Style: Eclipse. Composition: PVC Coated polyester scrim fabric for signs. Weight: 13oz/440 g. Thickness: 38 mm. End Use: Banners & Signs.

Tested For: **Brenda Siemer**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: NFPA 701-96 TM#2 Flat MEA WL 285

Tel: 1-(973)-627-8608 **Ext:** 119
Fax: 1-(973)-627-8506

PRECONDITIONING: [x] 1 hr @ 220°F (Standard)
[ ] 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

CONVERSION FACTORS: mm ÷ 25.4 = inches
g/m² ÷ 28.35 x .835 = oz/yd²

REMARKS:
None.

CERTIFICATION:
I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 1996 Edition Test Method #2 Flat Sheet Specimens.

Heather E. Robertson

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. /jd

MS. HEATHER ROBERTSON

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from The Govmark Organization, Inc.

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received: 11/17/2005	Completed: 12/14/2005	Letter: A2	her	P.O.#:	Test Report #: 2-60255-2-
Client's Identification	Lot No.: 10165. Date of Mfg.: 8/3/05. Style: Eclipse. Composition: PVC Coated polyester scrim fabric for signs. Weight: 13oz/440 g. Thickness: 38 mm. End Use: Banners & Signs.				

Tested For: Brenda Siemer
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: NFPA 701-96 TM#2 Flat MEA AW 1685

Tel: 1-(973)-627-8608 **Ext:** 119
Fax: 1-(973)-627-8506

Test Category: NFPA 701-96 TM2 Specifier: NYC Flex Signs CODE: 285-435-1685

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Resistant Textiles and Films 1996 Edition - Test Method #2 - Flat Sheet Specimens
as cited by The City of New York Department of Buildings Technical Policy and Procedure Notice #11/99 - Safety Standards for the Erection of Flex Sign Structures

SPECIMEN CONFIGURATION: [x] Single Layer; [ ] Multi Layer

RESULTS REPORTED: [ ] Initially
[ ] After 72 hours water leaching
[x] After 100 hours accelerated weathering

RESULTS: Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	286
2	0	0	260
3	0	0	300
4	0	0	265
5	0	0	283
6	0	0	240
7	0	0	224
8	0	0	244
9	0	0	270
10	0	0	235

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 517 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

[x] Passes; [ ] Fails; [ ] Requires testing of 5 additional specimens

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received: 11/17/2005	Completed: 12/14/2005	Letter: A2	her	P.O.#:	Test Report #: 2-60255-2-

Client's Identification	Lot No.: 10165. Date of Mfg.: 8/3/05. Style: Eclipse. Composition: PVC Coated polyester scrim fabric for signs. Weight: 13oz/440 g. Thickness: 38 mm. End Use: Banners & Signs.

Tested For: **Brenda Siemer**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: NFPA 701-96 TM#2 Flat MEA AW 1685

Tel: 1-(973)-627-8608 **Ext:** 119
Fax: 1-(973)-627-8506

PRECONDITIONING: [ ] 1 hr @ 220°F (Standard)
[x] 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

CONVERSION FACTORS: mm ÷ 25.4 = inches
g/m² ÷ 28.35 x .835 = oz/yd²

REMARKS:
None.

CERTIFICATION:
I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 1996 Edition Test Method #2 Flat Sheet Specimens.

Heather P. Robertson
AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. /rb AH

MS. HEATHER ROBERTSON

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from The Govmark Organization, Inc.

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received: 11/17/2005	Completed: 11/22/2005	Letter: A3	her	P.O.#:	Test Report #: 2-60255-3-

Client's Identification Lot No.: 10165. Date of Mfg.: 8/3/05. Style: Eclipse. Composition: PVC Coated polyester scrim fabric for signs. Weight: 13oz/440 g. Thickness: 38 mm. End Use: Banners & Signs.

Tested For: **Brenda Siemer**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: CA 1237 Sm 95

Tel: 1-(973)-627-8608 **Ext:** 119
Fax: 1-(973)-627-8506

PC: 1H /jd

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 Fire Resistance; Small Scale Test - EXTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED: [x] Initially
[ ] After 72 hrs water leaching
[ ] After 100 hrs weathering

RESULTS:

	Specimen #	Afterflame (seconds)	Char Length (inches)
Length:	1	0.0	4.0
	2	0.0	4.4
	3	1.0	4.6
Width:	4	0.0	4.3
	5	1.0	4.5
	6	1.0	3.8
	Avg:	0.5	4.3

REMARKS: None.

ACCEPTANCE CRITERIA:

Afterflame (seconds)	Char Length (inches)
2.0 maximum average	6.0 maximum average

CONCLUSION:

[x] The above results indicate compliance.

[ ] The above results indicate noncompliance.

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received: 11/17/2005	Completed: 11/22/2005	Letter: A3	her	P.O.#:	Test Report #: 2-60255-3-

Client's Identification	Lot No.: 10165. Date of Mfg.: 8/3/05. Style: Eclipse. Composition: PVC Coated polyester scrim fabric for signs. Weight: 13oz/440 g. Thickness: 38 mm. End Use: Banners & Signs.

Tested For: **Brenda Siemer**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: CA 1237 Sm 95

Tel: 1-(973)-627-8608 **Ext:** 119
Fax: 1-(973)-627-8506

Note: In August of 1993 the State Fire Marshal issued a proposed revision, which permitted a maximum average afterflame of 4.0 seconds. This proposed revision was honored by the subsequent State Fire Marshals until approximately February 2004, at which time the State Fire Marshal's office reverted to the unrevised rule of 1 second maximum average for interior fabric; and 2.0 seconds maximum average for exterior fabric.

With regard to Char Length acceptance, please refer to Govmark's document "California Title 19 Section 1237" dated August 11, 2005.

CERTIFICATION:
I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Fire Marshal Title 19: Section 1237 Small Scale.

Heather E. Robertson

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. /jd

MS. HEATHER ROBERTSON

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from The Govmark Organization, Inc.

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received: 11/17/2005	Completed: 11/28/2005	Letter: A4	her	P.O.#:	Test Report #: 2-60255-4-

Client's Identification Lot No.: 10165. Date of Mfg.: 8/3/05. Style: Eclipse. Composition: PVC Coated polyester scrim fabric for signs. Weight: 13oz/440 g. Thickness: 38 mm. End Use: Banners & Signs.

Tested For: **Brenda Siemer**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: CA 1237 Sm WL 95

Tel: 1-(973)-627-8608 **Ext:** 119
Fax: 1-(973)-627-8506

PC: 1H /jd

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 Fire Resistance; Small Scale Test - EXTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED: [ ] Initially
[x] After 72 hrs water leaching
[ ] After 100 hrs weathering

RESULTS:

	Specimen #	Afterflame (seconds)	Char Length (inches)
Length:	1	0	4.1
	2	0	3.9
	3	0	4.2
Width:	4	0	3.7
	5	0	3.3
	6	0	3.4
	Avg:	0	3.8

REMARKS: None.

ACCEPTANCE CRITERIA:

Afterflame (seconds)	Char Length (inches)
2.0 maximum average	6.0 maximum average

CONCLUSION:

[x] The above results indicate compliance.

[ ] The above results indicate noncompliance.

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received: 11/17/2005	Completed: 11/28/2005	Letter: A4	her	P.O.#:	Test Report #: 2-60255-4-

Client's Identification: Lot No.: 10165. Date of Mfg.: 8/3/05. Style: Eclipse. Composition: PVC Coated polyester scrim fabric for signs. Weight: 13oz/440 g. Thickness: 38 mm. End Use: Banners & Signs.

Tested For: **Brenda Siemer**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: CA 1237 Sm WL 95

Tel: 1-(973)-627-8608 **Ext:** 119
Fax: 1-(973)-627-8506

Note: In August of 1993 the State Fire Marshal issued a proposed revision, which permitted a maximum average afterflame of 4.0 seconds. This proposed revision was honored by the subsequent State Fire Marshals until approximately February 2004, at which time the State Fire Marshal's office reverted to the unrevised rule of 1 second maximum average for interior fabric; and 2.0 seconds maximum average for exterior fabric.

With regard to Char Length acceptance, please refer to Govmark's document "California Title 19 Section 1237" dated August 11, 2005.

CERTIFICATION:
I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Fire Marshal Title 19: Section 1237 Small Scale.

Heather E. Robertson

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. /jd

MS. HEATHER ROBERTSON

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from The Govmark Organization, Inc.

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received: 11/17/2005	Completed: 12/01/2005	Letter: A5	her	P.O.#:	Test Report #: 2-60255-5-

Client's Identification Lot No.: 10165. Date of Mfg.: 8/3/05. Style: Eclipse. Composition: PVC Coated polyester scrim fabric for signs. Weight: 13oz/440 g. Thickness: 38 mm. End Use: Banners & Signs.

Tested For: **Brenda Siemer**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: CA 1237 Sm AW 795

Tel: 1-(973)-627-8608 **Ext:** 119
Fax: 1-(973)-627-8506

PC: 1H /jd

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 Fire Resistance; Small Scale Test - EXTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED: [ ] Initially
[ ] After 72 hrs water leaching
[x] After 100 hrs weathering

RESULTS:

	Specimen #	Afterflame (seconds)	Char Length (inches)
Length:	1	0	4.1
	2	0	3.5
	3	0	4.7
Width:	4	0	3.6
	5	0	4.5
	6	0	3.9
	Avg:	0	4.1

REMARKS: None.

ACCEPTANCE CRITERIA:

Afterflame (seconds)	Char Length (inches)
2.0 maximum average	6.0 maximum average

CONCLUSION:

[x] The above results indicate compliance.

[ ] The above results indicate noncompliance.

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received: 11/17/2005	Completed: 12/01/2005	Letter: A5	her	P.O.#:	Test Report #: 2-60255-5-

Client's Identification: Lot No.: 10165. Date of Mfg.: 8/3/05. Style: Eclipse. Composition: PVC Coated polyester scrim fabric for signs. Weight: 13oz/440 g. Thickness: 38 mm. End Use: Banners & Signs.

Tested For: **Brenda Siemer**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: CA 1237 Sm AW 795

Tel: 1-(973)-627-8608 **Ext:** 119
Fax: 1-(973)-627-8506

Note: In August of 1993 the State Fire Marshal issued a proposed revision, which permitted a maximum average afterflame of 4.0 seconds. This proposed revision was honored by the subsequent State Fire Marshals until approximately February 2004, at which time the State Fire Marshal's office reverted to the unrevised rule of 1 second maximum average for interior fabric; and 2.0 seconds maximum average for exterior fabric.

With regard to Char Length acceptance, please refer to Govmark's document "California Title 19 Section 1237" dated August 11, 2005.

CERTIFICATION:
I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Fire Marshal Title 19: Section 1237 Small Scale.

Heather E. Robertson

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. /jd

MS. HEATHER ROBERTSON

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from The Govmark Organization, Inc.

CALIFORNIA DEPARTMENT OF FORESTRY and FIRE PROTECTION
OFFICE OF THE STATE FIRE MARSHAL

REGISTERED FLAME RESISTANT PRODUCT

Product:
NORMANDY-ECLIPSE FL

Registration No.
F-77601

Product Marketed By:
ULTRAFLEX SYSTEMS
1578 SUSSEX TPK., BLDG. #4
RANDOLPH, NJ 07869

This product meets the minimum requirements of flame resistance established by the California State Fire Marshal for products identified in Section 13115, California Health and Safety Code.

The scope of the approved use of this product is provided in the current edition of the **CALIFORNIA APPROVED LIST OF FLAME RETARDANT CHEMICALS AND FABRICS, GENERAL AND LIMITED APPLICATIONS CONCERNS** published by the California State Fire Marshal.

Deputy State Fire Marshal

Expire: 6/30/2016

FR-8

CITY OF NEW YORK
DEPARTMENT OF BUILDINGS

Pursuant to Administrative Code Section 27-131, the following equipment or material has been found acceptable for use in accordance with the Report of Materials and Equipment Acceptance (MEA) Division.

Richard C. Visconti, R.A., Acting Commissioner
MEA 67-00-M
Report of Material and Equipment Acceptance Division

Manufacturer - Ultraflex System, Inc., 385 Franklin Avenue, Rockaway, New Jersey 07866.
Trade Name – Eclipse.
Product - PVC coated fabric for flex sign.
Pertinent Code Section(s) -27-499, 27-501, 27-506, 27-507, and TPPN #11/99.
Prescribed Test(s) - RS 7-3 [NFPA 701 (Test Method 2)].
Laboratory – Magil Laboratory.
Test Report(s) - Test Report #QLL 18030, dated March 1, 2000.
Description - The material is an extruded flame retardant PVC with the base fabric being a 2.23 oz. polyester 9x9 with a 1000 denier. The membrane when extruded has 5.86 oz. of flame retardant PVC laminated to the face and 3.91 oz. of flame retardant PVC laminated to the back. The intended application is for billboard applications.

Recommendation - That the above material be accepted as meeting the flame resistance requirements of Section 27-506 and 27-507 of the Building Code, for use on flex signs. The acceptance of this material is limited to flame resistance only. Structural and other requirements shall be in accordance with pertinent Building Code provisions and Technical Policy and Procedure Notice #11/99. All installations, uses and locations shall be in accordance with the New York City Building Code, specifically with Section 27-499 and 27-501, and the Zoning Resolution. All shipments and deliveries of such materials shall, in addition, be accompanied by a tag, certifying that the materials shipped or delivered is equivalent to those tested and accepted for use, as provided for in Section 27-131 of the Building Code.

Final Acceptance MAY 25 2000

Examined By S Derkhudar