The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received:06/15/2010	Completed:06/22/2010	Letter: W	rb	P.O.#:	Test Report #:	2-83691-0-
Client's Identification	Style: SuperPrint Plus. Content: Polyester. Weight: 13 oz/yd². End Use: Signs, Banners, Billboards, Etc.					

Tested For: **Jaime L. Giannantonio**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: NFPA 701-2010 TM#2 Flat 340

Tel: 1-(973)-627-8608 **Ext:** 124
Fax: 1-(973)-627-8506

PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2010 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: [x] Single Layer; [ ] Multi Layer

RESULTS REPORTED: [x] Initially [ ] After 72 hours water leaching
[ ] After 3 dry cleanings [ ] After 100 hours accelerated weathering
[ ] After 5 launderings @ 160°F

RESULTS:

Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	210
2	0	0	260
3	0	0	240
4	0	0	370
5	0	0	230
6	0	0	290
7	0	0	250
8	0	0	310
9	0	0	230
10	0	0	300

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 427 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

[x] Passes; [ ] Fails; [ ] Requires testing of 5 additional specimens

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2010 Edition Test Method #2 Flat Sheet Specimens.

Heather E. Robertson

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. /jb/ mg (Page 1 of 2)

MS. HEATHER ROBERTSON AUG 2 2010

File Copy

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received:06/15/2010	Completed:06/22/2010	Letter: W	rb	P.O.#:	Test Report #:	2-83691-0-
Client's Identification	Style: SuperPrint Plus. Content: Polyester. Weight: 13 oz/yd². End Use: Signs, Banners, Billboards, Etc.					

Tested For: **Jaime L. Giannantonio**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: NFPA 701-2010 TM#2 Flat 340

Tel: 1-(973)-627-8608 **Ext:** 124
Fax: 1-(973)-627-8506

PRECONDITIONING: [x] 1 hr @ 220°F (Standard)
[ ] 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS:
None.

CONVERSION FACTORS:
mm ÷ 25.4 = inches
g/m² ÷ 28.35 x .835 = oz/yd²

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from The Govmark Organization, Inc.

File Copy

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received:06/15/2010	Completed:07/02/2010	Letter: W1	rb	P.O.#:	Test Report #:	2-83691-1-
Client's Identification	Style: SuperPrint Plus. Content: Polyester. Weight: 13 oz/yd². End Use: Signs, Banners, Billboards, Etc.					

Tested For: **Jaime L. Giannantonio**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: NFPA 701-2010 TM#2 Flat WL 490

Tel: 1-(973)-627-8608 **Ext:** 124
Fax: 1-(973)-627-8506

PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2010 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: [x] Single Layer; [ ] Multi Layer

RESULTS REPORTED: [ ] Initially
[ ] After 3 dry cleanings
[ ] After 5 launderings @ 160°F
[x] After 72 hours water leaching
[ ] After 100 hours accelerated weathering

RESULTS:

Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	130
2	0	0	240
3	0	0	240
4	0	0	320
5	0	0	250
6	0	0	240
7	0	0	250
8	0	0	180
9	0	0	240
10	0	0	250

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 427 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

[x] Passes; [ ] Fails; [ ] Requires testing of 5 additional specimens

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2010 Edition Test Method #2 Flat Sheet Specimens.

Heather E. Robertson

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. /jb/ MG

MS. HEATHER ROBERTSON

File Copy

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received:06/15/2010	Completed:07/02/2010	Letter: W1	rb	P.O.#:	Test Report #:	2-83691-1-
Client's Identification	Style: SuperPrint Plus. Content: Polyester. Weight: 13 oz/yd². End Use: Signs, Banners, Billboards, Etc.					

Tested For: **Jaime L. Giannantonio**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: NFPA 701-2010 TM#2 Flat WL 490

Tel: 1-(973)-627-8608 **Ext:** 124
Fax: 1-(973)-627-8506

PRECONDITIONING: [x] 1 hr @ 220°F (Standard)
[ ] 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS:
None.

CONVERSION FACTORS:
mm ÷ 25.4 = inches
g/m² ÷ 28.35 x .835 = oz/yd²

(Page 2 of 2)

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from The Govmark Organization, Inc.

File Copy

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received:06/15/2010	Completed:08/10/2010	Letter: W2	rb	P.O.#:	Test Report #:	2-83691-2-
Client's Identification	Style: SuperPrint Plus. Content: Polyester. Weight: 13 oz/yd². End Use: Signs, Banners, Billboards, Etc.					

Tested For: **Jaime L. Giannantonio**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: NFPA 701-2010 TM#2 Flat AW 1940

Tel: 1-(973)-627-8608 **Ext:** 124
Fax: 1-(973)-627-8506

PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2010 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: [x] Single Layer; [ ] Multi Layer

RESULTS REPORTED: [ ] Initially [ ] After 72 hours water leaching
[ ] After 3 dry cleanings [x] After 100 hours accelerated weathering
[ ] After 5 launderings @ 160°F

RESULTS:

Specimen #	Afterflame Length (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	170
2	0	0	190
3	0	0	170
4	0	0	130
5	0	0	160
6	0	0	200
7	0	0	160
8	0	0	170
9	0	0	140
10	0	0	170

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 427 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

[x] Passes; [ ] Fails; [ ] Requires testing of 5 additional specimens

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2010 Edition Test Method #2 Flat Sheet Specimens.

Heather E. Roberts

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. /jb/mg

MS. HEATHER ROBERTSON

File Copy

The Govmark Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received:06/15/2010	Completed:08/10/2010	Letter: W2	rb	P.O.#:	Test Report #:	2-83691-2-
Client's Identification	Style: SuperPrint Plus. Content: Polyester. Weight: 13 oz/yd². End Use: Signs, Banners, Billboards, Etc.					

Tested For: **Jaime L. Giannantonio**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: NFPA 701-2010 TM#2 Flat AW 1940

Tel: 1-(973)-627-8608 **Ext:** 124
Fax: 1-(973)-627-8506

PRECONDITIONING: [x] 1 hr @ 220°F (Standard)
[ ] 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS:
None.

CONVERSION FACTORS:
mm ÷ 25.4 = inches
g/m² ÷ 28.35 x .835 = oz/yd²

(Page 2 of 2)

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from The Govmark Organization, Inc.

File Copy

NYC BUILDINGS

NYC Department of Buildings
280 Broadway, New York, NY 10007
Patricia Lancaster, FAIA, Commissioner
(212) 566-5000, TTY: (212) 566-4769

Report of Materials and Equipment Acceptance Division

Pursuant to Administrative Code Section 27-131, the following equipment or material has been found acceptable for use subject to the terms and conditions contained herein.

MEA 287-07-M

Manufacturer:	Ultraflex Systems Inc., 1578 Sussex Turnpike, Building #4, Randolph, N.J. 07869
Trade Name(s):	SuperPrint
Product:	PVC-coated vinyl material
Pertinent Code Section(s):	27-499, 27-501, 27-506, 27-507, TPPN #11/99
Prescribed Test(s):	RS 7-3 (NFPA 701-Test Method 2)
Laboratory:	The Govmark Organization
Test Report(s):	Report Nos. 2-61183-0, 2-61183-1, 2-61183-2-RP, issued February 16, 2006.

Description: PVC-coated vinyl material for digital and screen printing for in- or outdoor-signs, banners and billboards. Material weighs 12 ozs. per square yard.

Terms and Conditions: The above-described material is accepted with the following conditions:

1. The acceptance of this material is limited to flame resistance.
2. Structural and other requirements shall be in accordance with pertinent Building Code provisions and Technical Policy and Procedure Notice #11/99.

3. All installations, uses and locations shall be in accordance with the New York City Building Code, specifically with Section 27-499 and 27-501, and the Zoning Resolution.

4. All shipments and deliveries of such material shall be provided with a label, suitably placed, certifying that the material shipped or delivered is equivalent to that tested and accepted for use, as provided in Section 27-131 of the New York City Building Code.

Note: In accordance with Section 27-131(d), all materials tested and accepted for use shall be subject to periodic retesting as determined by the Commissioner; and any material which upon retesting is found not to comply with Code requirements or the requirements set forth in the approval of the Commissioner shall cease to be acceptable for the use intended. During the period for such retesting, the Commissioner may require the use of such material to be restricted or discontinued if necessary to secure safety.

Final Acceptance September 19, 2007

Examined By Sean Derkhodam

Govmark

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Received:04/22/2015	Completed:04/24/2015	Letter: L	AM	P.O.#:	Test Report #:	3-07524-0-
Client's Identification	Style: Super Print Plus. Content: Polyester. End Use: Banner Material/Outdoor.					

Tested For: **Kylie Schleicher**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: CAN/ULC-S109-14 Small Flame Test 195

Tel: 1-(973)-627-8608 **Ext:**
Fax: 1-( )- -

Test Category: CAN/UL Small Specifier: CAN/UL /jd

TEST PERFORMED: CAN/ULC-S109-14 * - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Small Flame Test

(* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

PRECONDITIONING:

[x] Standard method: 0.5 hour @ 105 ± 2°C

[ ] Alternate method for materials that are affected by heating to 105°C:

[ ] Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH

[ ] Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by Govmark): 419 gm/m²

CONVERSION FACTORS:

mm ÷ 25.4 = inches
g/m² ÷ 28.35 x 0.0835 = oz/yd²

RESULTS ARE REPORTED:

[x] Initially	[code 195]
[ ] After 10 dry cleanings	[code 395]
[ ] After 10 launderings	[code 345]
[ ] After 72 hours water leaching	[code 345]
[ ] After scrubbing	[code 545]
[ ] After 360 hours accelerated weathering	[code 4775]

Govmark

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Received: 04/22/2015	Completed: 04/24/2015	Letter: L	AM	P.O.#:	Test Report #: 3-07524-0-
Client's Identification	Style: Super Print Plus. Content: Polyester. End Use: Banner Material/Outdoor.				

Tested For: **Kylie Schleicher**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: CAN/ULC-S109-14 Small Flame Test 195

Tel: 1-(973)-627-8608 **Ext:**
Fax: 1-( )- -

RESULTS:	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Damaged Length (mm)
Length:	1	7.6	0	148
	2	0.0	0	154
	3	0.0	0	139
	4	0.0	0	160
	5	0.0	0	142
Width:	6	0.0	0	136
	7	0.0	0	135
	8	0.0	0	142
	9	0.0	0	133
	10	0.0	0	130
			Avg:	142

REMARKS: None.

ACCEPTANCE CRITERIA:	Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
Maximum Average:	**	Not specified	165 mm (6.5")
Maximum Individual Specimen:	**	2.0	190 mm (7.5")

(** Surface Flaming values are required to be reported after removal of the 12 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

[x] Complies; [ ] Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by CAN/ULC-S109-14.

MS. PHYLLIS PETTIT

AUTHORIZED SIGNATURE
GOVMARK
/ec /tm

MAY 0 1 2015

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from Govmark.