



CALIFORNIA DEPARTMENT OF FORESTRY and FIRE PROTECTION
OFFICE OF THE STATE FIRE MARSHAL

REGISTERED FLAME RESISTANT PRODUCT

Product:

DSS 120Z BLOCKOUT

Registration No.

F-93401

Product Marketed By:

ULTRAFLEX SYSTEMS INC
1578 SUSSEX TURNPIKE, BLDG 4
RANDOLPH, NJ 07869

This product meets the minimum requirements of flame resistance established by the California State Fire Marshal for products identified in Section 13115, California Health and Safety Code.

The scope of the approved use of this product is provided in the current edition of the **CALIFORNIA APPROVED LIST OF FLAME RETARDANT CHEMICALS AND FABRICS, GENERAL AND LIMITED APPLICATIONS CONCERNS** published by the California State Fire Marshal.

Deputy State Fire Marshal

Expire: 6/30/2017



Received: 04/06/2009 Completed: 04/08/2009 Letter: D rb P.O.#: Test Report #: 2-78072-0-

Client's Identification: Descor-Decorative Fabric For Indoor Walls and Ceilings.

Tested For: **Jaime L. Giannantonio** Key Test: CA 1237 Sm 105
 Ultraflex Systems Inc.
 1578 Sussex Tpk., Bldg. #4
 Randolph, NJ 07869
 Tel: 1-(973)-627-8608 Ext: 124
 Fax: 1-(973)-627-8506

PC: 1H /jd

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - EXTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED: [x] Initially
 [] After 72 hours water leaching
 [] After 100 hours weathering

RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)
Warp:	1	0	0	5.6
	2	0	0	4.3
	3	0	0	4.5
	4	0	0	4.4
	5	0	0	4.4
	Avg:	0		
Fill:	6	0	0	4.3
	7	0	0	3.5
	8	0	0	3.2
	9	0	0	4.0
	10	0	0	3.6
	Avg:	0		

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 7.4 oz/yd²

ACCEPTANCE CRITERIA:
 Afterflame: 4.0 seconds maximum avg for length or width
 Afterglow: (see Note #2 below)
 Char Length: 6.0" maximum for any individual specimen

- Notes:
1. An asterisk (*) next to any char length measurements indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd².
 2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.

Received: 04/06/2009	Completed: 04/08/2009	Letter: D	rb	P.O.#:	Test Report #:	2-78072-0-
Client's Identification	Descor-Decorative Fabric For Indoor Walls and Ceilings.					
Tested For: Jaime L. Giannantonio			Key Test: CA 1237 Sm		105	
Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869			Tel: 1-(973)-627-8608 Fax: 1-(973)-627-8506		Ext: 124	

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:


Complies; Does not comply

REMARKS: None.

NOTE: In August 1993 the State Fire Marshal issued a proposed revision, which permitted a maximum average afterflame of 4.0 seconds. This proposed revision was honored by the subsequent State Fire Marshal until approximately February 2004, at which time the State Fire Marshal's office reverted to the unrevised rule of 2.0 seconds maximum average for exterior fabric.

In a conversation with the latest California State Fire Marshal on August 9, 2007, it was learned that the proposed 1993 revision is now back in effect. In addition to allowing 4 seconds Afterflame rather than 2 seconds, the proposed revision provides for testing of 10 specimens, rather than 6 specimens.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93).



AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. /mg

MS. HEATHER ROBERTSON
MAY 0 1 2009

(Page 2 of 2)

Received: 04/06/2009 Completed: 04/16/2009 Letter: D1 rb P.O.#: Test Report #: 2-78072-1-

Client's Identification Descor-Decorative Fabric For Indoor Walls and Ceilings.

Tested For: **Jaime L. Giannantonio** Key Test: CA 1237 Sm WL 105
 Ultraflex Systems Inc.
 1578 Sussex Tpk., Bldg. #4
 Randolph, NJ 07869
 Tel: 1-(973)-627-8608 Ext: 124
 Fax: 1-(973)-627-8506

PC: 1H /jd

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - EXTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED: [] Initially
 [x] After 72 hours water leaching
 [] After 100 hours weathering

RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)
Warp:	1	0	0	5.0
	2	0	0	4.8
	3	0	0	4.8
	4	0	0	4.4
	5	0	0	3.7
	Avg:	0		
Fill:	6	0	0	2.4
	7	0	0	3.8
	8	0	0	3.7
	9	0	0	4.1
	10	0	0	3.6
	Avg:	0		

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 7.4 oz/yd²

ACCEPTANCE CRITERIA:

Afterflame: 4.0 seconds maximum avg for length or width
 Afterglow: (see Note #2 below)
 Char Length: 6.0" maximum for any individual specimen

Notes:

1. An asterisk (*) next to any char length measurements indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd².
2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.



Received: 04/06/2009	Completed: 04/16/2009	Letter: D1	rb	P.O.#:	Test Report #:	2-78072-1-
Client's Identification	Descor-Decorative Fabric For Indoor Walls and Ceilings.					
Tested For:	Jaime L. Giannantonio	Key Test: CA 1237 Sm WL			105	
	Ultraflex Systems Inc.					
	1578 Sussex Tpk., Bldg. #4	Tel: 1-(973)-627-8608			Ext: 124	
	Randolph, NJ 07869	Fax: 1-(973)-627-8506				

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply

REMARKS: None.

NOTE: In August 1993 the State Fire Marshal issued a proposed revision, which permitted a maximum average afterflame of 4.0 seconds. This proposed revision was honored by the subsequent State Fire Marshal until approximately February 2004, at which time the State Fire Marshal's office reverted to the unrevised rule of 2.0 seconds maximum average for exterior fabric.

In a conversation with the latest California State Fire Marshal on August 9, 2007, it was learned that the proposed 1993 revision is now back in effect. In addition to allowing 4 seconds Afterflame rather than 2 seconds, the proposed revision provides for testing of 10 specimens, rather than 6 specimens.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93).

Heather E. Robertson

AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC.

/jrb/mqj

MS. HEATHER ROBERTSON

(Page 2 of 2)

MAY 01 2009

Received: 04/06/2009 Completed: 04/27/2009 Letter: D2 rb P.O.#: Test Report #: 2-78072-2-

Client's Identification Descor-Decorative Fabric For Indoor Walls and Ceilings.

Tested For: **Jaime L. Giannantonio** Key Test: CA 1237 Sm AW 105
 Ultraflex Systems Inc.
 1578 Sussex Tpk., Bldg. #4
 Randolph, NJ 07869
 Tel: 1-(973)-627-8608 Ext: 124
 Fax: 1-(973)-627-8506

PC: 1H /jd

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - EXTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED: [] Initially
 [] After 72 hours water leaching
 [x] After 100 hours weathering

RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)
Warp:	1	0	0	4.2
	2	0	0	3.5
	3	0	0	3.9
	4	0	0	3.9
	5	0	0	4.6
	Avg:	0		
Fill:	6	0	0	4.1
	7	0	0	3.6
	8	0	0	3.3
	9	0	0	4.4
	10	0	0	4.3
	Avg:	0		

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 7.4 oz/yd²

ACCEPTANCE CRITERIA:

Afterflame: 4.0 seconds maximum avg for length or width
 Afterglow: (see Note #2 below)
 Char Length: 6.0" maximum for any individual specimen

- Notes:
1. An asterisk (*) next to any char length measurements indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd².
 2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.

Received: 04/06/2009	Completed: 04/27/2009	Letter: D2	rb	P.O.#:	Test Report #: 2-78072-2-
----------------------	-----------------------	------------	----	--------	---------------------------

Client's Identification Descor-Decorative Fabric For Indoor Walls and Ceilings.

Tested For: Jaime L. Giannantonio Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869	Key Test: CA 1237 Sm AW Tel: 1-(973)-627-8608 Fax: 1-(973)-627-8506	105 Ext: 124
--	--	----------------------------

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:


Complies; Does not comply

REMARKS: None.

NOTE: In August 1993 the State Fire Marshal issued a proposed revision, which permitted a maximum average afterflame of 4.0 seconds. This proposed revision was honored by the subsequent State Fire Marshal until approximately February 2004, at which time the State Fire Marshal's office reverted to the unrevised rule of 2.0 seconds maximum average for exterior fabric.

In a conversation with the latest California State Fire Marshal on August 9, 2007, it was learned that the proposed 1993 revision is now back in effect. In addition to allowing 4 seconds Afterflame rather than 2 seconds, the proposed revision provides for testing of 10 specimens, rather than 6 specimens.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93).



AUTHORIZED SIGNATURE
 THE GOVMARK ORGANIZATION, INC.

/jb/mgj

MS. HEATHER ROBERTSON

(Page 2 of 2)

MAY 01 2009