



Received:06/26/2013 Completed:06/28/2013 Letter: P AA P.O.#: Test Report #: 2-97533-0-

Client's Identification Style: Ultima Pro FL. Content: Polyester. End Use: Bill Boards, Banners.

Tested For: **Jaime Sherman** Key Test: NFPA 701-2010 TM#2 Flat 375  
 Ultraflex Systems Inc. Tel: 1-(973)-627-8608 Ext:  
 1578 Sussex Tpk., Bldg. #4 Fax: 1-(973)-627-8506  
 Randolph, NJ 07869

PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2010 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION:  Single Layer;  Multi Layer

RESULTS REPORTED:  Initially  After 72 hours water leaching  
 After 3 dry cleanings  After 100 hours accelerated weathering  
 After 5 launderings @ 160°F

Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	176
2	0	0	141
3	0	0	168
4	0	0	145
5	0	0	166
6	0	0	179
7	0	0	158
8	0	0	173
9	0	0	154
10	0	0	169

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 456 g/m²

FAILURE CRITERIA: For each individual specimen ---

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

Passes;  Fails;  Requires testing of 5 additional specimens



Received:06/26/2013	Completed:06/28/2013	Letter: P	AA	P.O.#:	Test Report #:	2-97533-0-
Client's Identification	Style: Ultima Pro FL. Content: Polyester. End Use: Bill Boards, Banners.					
Tested For: <b>Jaime Sherman</b>	Key Test: NFPA 701-2010 TM#2 Flat					375
Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869	Tel: 1-(973)-627-8608		Ext:			Fax: 1-(973)-627-8506

PRECONDITIONING:     1 hr @ 220°F (Standard)  
                               24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS: None.

CONVERSION FACTORS:

mm ÷ 25.4 = inches  
g/m<sup>2</sup> ÷ 28.35 x .835 = oz/yd<sup>2</sup>

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2010 Edition Test Method #2 Flat Sheet Specimens

JUL 11 2013

AUTHORIZED SIGNATURE  
THE GOVMARK ORGANIZATION, INC. /jb

ig<sup>b</sup>

**MS. PHYLLIS PETTIT**

(Page 2 of 2)