

Received: 02/01/2010 Completed: 02/12/2010 Letter: X1 rb P.O.#: Test Report #: 2-82014-0-

Client's Identification: Ultra Canvas Heavy C285 Coated Heavy Canvas Textile. Weight (oz/yd<sup>2</sup>): 8.5. Content: Polyester

Tested For: **Jaime L. Giannantonio** Key Test: CA 1237 Sm 115  
 Ultraflex Systems Inc.  
 1578 Sussex Tpk., Bldg. #4 Tel: 1-(973)-627-8608 Ext: 124  
 Randolph, NJ 07869 Fax: 1-(973)-627-8506

PC: 1H /jd

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - EXTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED:  Initially  
 After 72 hours water leaching  
 After 100 hours weathering

RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)
Warp:	1	0.0	0	4.2
	2	0.0	0	3.5
	3	11.0	0	4.5
	4	0.0	0	3.6
	5	0.0	0	4.2
	Avg:	2.2		
Fill:	6	0.0	0	4.0
	7	0.0	0	3.0
	8	20.0	0	3.1
	9	0.0	0	3.5
	10	0.0	0	3.5
	Avg:	4.0		

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 8.4 oz/yd<sup>2</sup>

ACCEPTANCE CRITERIA:

Afterflame: 4.0 seconds maximum avg for length or width  
 Afterglow: (see Note #2 below)  
 Char Length: 6.0" maximum for any individual specimen

Notes:

1. An asterisk (\*) next to any char length measurements indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd<sup>2</sup>.
2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.



Received:02/01/2010	Completed:02/12/2010	Letter: X1	rb	P.O.#:	Test Report #:	2-82014-0-
Client's Identification	Ultra Canvas Heavy C285 Coated Heavy Canvas Textile. Weight (oz/yd <sup>2</sup> ): 8.5. Content: Polyester					
Tested For: <b>Jaime L. Giannantonio</b>	Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869				Key Test: CA 1237 Sm	115
					Tel: 1-(973)-627-8608	Ext: 124
					Fax: 1-(973)-627-8506	

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies;     Does not comply

REMARKS: None.

NOTE: In August 1993 the State Fire Marshal issued a proposed revision, which permitted a maximum average afterflame of 4.0 seconds. This proposed revision was honored by the subsequent State Fire Marshal until approximately February 2004, at which time the State Fire Marshal's office reverted to the unrevised rule of 2.0 seconds maximum average for exterior fabric.

In a conversation with the latest California State Fire Marshal on August 9, 2007, it was learned that the proposed 1993 revision is now back in effect. In addition to allowing 4 seconds Afterflame rather than 2 seconds, the proposed revision provides for testing of 10 specimens, rather than 6 specimens. This information has been verified current per an August 26, 2009 conversation with the California State Fire Marshall.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93).

*Heather E. Robertson*

AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC. / ec/mg

**MS. HEATHER ROBERTSON**

MAR 01 2010

(Page 2 of 2)