

CITY OF NEW YORK  
DEPARTMENT OF BUILDINGS

Pursuant to Administrative Code Section 27-131, the following equipment or material has been found acceptable for use in accordance with the Report of Materials and Equipment Acceptance (MEA) Division.

Patricia J. Lancaster, A.I.A., Commissioner  
MEA 205-00-M Vol. II

Report of Material and Equipment Acceptance Division

Manufacturer – Ultraflex System, Inc., 385 Franklin Avenue, Rockaway, New Jersey  
07866.

Trade Name – Ultralon IV.

Product - PVC coated fabric for flex sign.

Pertinent Code Section(s) -27-499, 27-501, 27-506, 27-507, and TPPN#11/99.

Prescribed Test(s) - RS 7-3 [NFPA 701(Test Method 2)].

Laboratory - Govmark Organization Inc.


Test Report(s) - Test Report #2-38691-0-(RE) dated January 7, 2002, 2-38691-1 dated  
January 15, 2002, and 2-38691-2 dated February 4, 2002.

Description –Ultralon IV material for use as flex sign, is a polyester fabric coated  
with PVC vinyl. It is used for large hanging banners and signs. It can be  
printed on. The flexsign has 19.5 oz./yd<sup>2</sup> (ten widths: 3'6" to 16'4").

Recommendation - That the above material be accepted as meeting the flame  
resistance requirements of Section 27-506 and 27-507 of the Building Code,  
for use on flex signs. The acceptance of this material is limited to flame  
resistance only. Structural and other requirements shall be in accordance  
with pertinent Building Code provisions and Technical Policy and Procedure  
Notice #11/99. All installations, uses and locations shall be in accordance  
with the New York City Building Code, specifically with Section 27-499 and 27-  
501, and the Zoning Resolution. All shipments and deliveries of such  
materials shall, in addition, be accompanied by a tag, certifying that the  
materials shipped or delivered is equivalent to those tested and accepted for  
use, as provided for in Section 27-131 of the Building Code.

Final Acceptance April 26/2002

Examined By S. Derfhalan



# TEST REPORT

GRAFLEX SYSTEMS, INC.  
5 Franklin Avenue  
Skaway, NJ. 07866  
Attn. John Schleicher, Jr.

REPORT NO. 24815

February 8, 1999

PAGE 25 OF 40

## IDENTIFICATION SUBMITTED BY CLIENT

1 SAMPLE: **ULTRALON IV**

FIRE RESISTANCE  
(City of New York)

## EVALUATION OF TEST RESULTS

The item submitted DOES meet the above requirements when tested in accordance with Rules for Tests of Fire Resistive, Flameproofed Materials as specified by the City of New York Board of Standards and Appeals under Calendar No. 94-40 S.R.

IF YOU NEED ASSISTANCE IN INTERPRETING THESE TESTS RESULTS  
OR IF YOU HAVE ANY QUESTIONS, PLEASE FEEL FREE TO CALL:  
HEATHER ROBERTSON OR EDUARDO PALOMO



Intertek  
Testing Services

LABTEST INTERNATIONAL, INC.

*Michele Payne*  
Michele Payne  
Technical Supervisor

Test Reference  
24815  
JG

-continued-



## TEST REPORT

PAGE 26 OF 40

REPORT NO. 24815

February 8, 1999

IDENTIFICATION SUBMITTED BY CLIENT1 SAMPLE: ULTRALON IVTEST RESULTS

	<u>FLASHING</u>	<u>AFTERFLAME (SECONDS)</u>	<u>AFTERGLOW AT EDGE OF CHAR (SECONDS)</u>
Warp	NO	0.0	0.0
Warp	NO	0.0	0.0
Warp	NO	0.0	0.0
Filling	NO	0.0	0.0
Filling	NO	0.0	0.0
Filling	NO	<u>0.0</u>	<u>0.0</u>
Average:		0.0	0.0

REQUIREMENTS

- No flashing shall occur at any time on the length of the specimen. (Flashing due to fuzz or bad edges may be disregarded).
- Average afterflame shall not exceed three seconds.
- Average afterglow at the edge of the charred area shall not exceed 20 seconds. (Glow confined to the charred area may be disregarded).