



Received: 12/10/2015	Completed: 12/11/2015	Letter: E	AM	P.O.#:	Test Report #:	3-10863-0-
Client's Identification	Style: Pole Banner Select. Composition: Polyester / PVC. End Use: Outdoor Banners.					
Tested For: Kylie Schleicher	Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869				Key Test: NFPA 701-2015 TM#2 Flat	445
					Tel: 1-(973)-627-8608	Ext:
					Fax: 1-()- -	

PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2015 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: Single Layer; Multi Layer

RESULTS REPORTED: Initially After 72 hours water leaching
 After 3 dry cleanings After 100 hours accelerated weathering
 After 5 launderings @ 160°F

RESULTS:

Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	268
2	0	0	218
3	0	0	246
4	0	0	184
5	0	0	207
6	0	0	198
7	0	0	183
8	0	0	198
9	0	0	223
10	0	0	184

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 641 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:


Passes; Fails; Requires testing of 5 additional specimens



96-D Allen Boulevard
 Farmingdale, New York 11735-5626 USA
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
 e-mail: testing@govmark.com

Received: 12/10/2015	Completed: 12/11/2015	Letter: E	AM	P.O.#:	Test Report #:	3-10863-0-
Client's Identification	Style: Pole Banner Select. Composition: Polyester / PVC. End Use: Outdoor Banners.					
Tested For: Kylie Schleicher	Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869				Key Test: NFPA 701-2015 TM#2 Flat	445
	Tel: 1-(973)-627-8608		Ext:			
	Fax: 1-()- -					

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2015 Edition Test Method #2 Flat Sheet Specimens.



 AUTHORIZED SIGNATURE
 GOVMARK
 /ec **lb9**

MS. PHYLLIS PETTIT
 DEC 16 2015

PRECONDITIONING: 1 hr @ 220°F (Standard)
 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS: Client requested that the restraining clamp binder clips be eliminated to replicate the provisions of the 1996 Test Method #1 version of this document.

CONVERSION FACTORS:
 mm ÷ 25.4 = inches
 g/m² ÷ 28.35 x .835 = oz/yd²