



96-D Allen Boulevard  
Farmingdale, New York 11735-5626 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
e-mail: testing@govmark.com

Page 1

Received:05/17/2018	Completed:05/21/2018	Letter: Q	MB	P.O.#:	Test Report #: 3-26134-0-
---------------------	----------------------	-----------	----	--------	---------------------------

Client's Identification	Style: Ultima Pro. Content: Polyester. End Use: Banners.
-------------------------	--

Tested For: **Kylie Schleicher**

Ultraflex Systems Inc.  
1578 Sussex Tpk., Bldg. #4  
Randolph, NJ 07869

Key Test: CAN/ULC-S109-14 Large Flame Test 395  
Single Sheet

Tel: 1-(973)-627-8608 Ext:

Fax: 1-( )- -

LE: 2014; V 09/15

Specifier: CAN/UL

NTR 04/16 /dl

Test Category: CAN/UL Large Flat

TEST PERFORMED: CAN/ULC-S109-14 \* - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Large Flame Test, Single Sheet Specimen

(\* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

PRECONDITIONING:

☒ Standard method: 0.5 hour @ 105 ± 2°C

☐ Alternate method for materials that are affected by heating to 105°C:

☐ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH

☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by Govmark): 432.5 g/m<sup>2</sup>

CONVERSION FACTORS:

mm ÷ 25.4 = inches

g/m<sup>2</sup> ÷ 28.35 x 0.0835 = oz/yd<sup>2</sup>

RESULTS ARE REPORTED:

☒ Initially

[code 395]

☐ After 10 dry cleanings

[code 595]

☐ After 10 launderings

[code 545]

☐ After 72 hours water leaching

[code 545]

☐ After scrubbing

[code 745]

☐ After 360 hours accelerated weathering

[code 5995]

<b>Received:</b> 05/17/2018	<b>Completed:</b> 05/21/2018	<b>Letter:</b> Q	<b>MB</b>	<b>P.O.#:</b>	<b>Test Report #:</b> 3-26134-0-
<b>Client's Identification</b>	Style: Ultima Pro. Content: Polyester. End Use: Banners.				
<b>Tested For:</b> <b>Kylie Schleicher</b> Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869			<b>Key Test:</b> CAN/ULC-S109-14 Large Flame Test 395 Single Sheet <b>Tel:</b> 1-(973)-627-8608 <b>Ext:</b> <b>Fax:</b> 1-( )- -		

RESULTS:	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Damaged Length (mm)
	-----	-----	-----	-----
Length:	1	0.0	0	31
	2	0.0	0	20
	3	0.0	0	15
	4	0.0	0	16
	5	0.0	0	41
Width:	6	0.0	0	10
	7	0.0	0	62
	8	0.0	0	19
	9	0.0	0	8
	10	8.0	0	25

REMARKS: None.

ACCEPTANCE CRITERIA:	Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
	-----	-----	-----
Maximum Average:	**	Not specified	Not specified
Maximum Individual Specimen:	**	2.0	250 mm

(\*\* Surface Flaming values are required to be reported after removal of the 120 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

☒ Complies; ☐ Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

  
 -----  
 AUTHORIZED SIGNATURE  
 SGS GOVMARK  
 /tm

Phyllis Pettit

MAY 24 2018

(Page 2 of 2)