



GOVMARK

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
email: govmark.accounting@sgs.com

Page 1

Received: 09/06/2018	Completed: 09/07/2018	Letter: V	BG	P.O.#:	Test Report #: 3-28236-0-
----------------------	-----------------------	-----------	----	--------	---------------------------

Client's Identification	Style: Ultra Poplin Pes S240. Content: Polyester. End Use: Banner.
-------------------------	--

Tested For: **Kylie Schleicher**

Ultraflex Systems Inc.

1578 Sussex Tpk., Bldg. #4

Randolph, NJ 07869

Key Test: CAN/ULC-S109-14 Small Flame Test 195

Tel: 1-(973)-627-8608

Ext:

Fax: 1-()- -

LE 2014; V 09/18

Specifier: CAN/UL

NTR 04/16

/dl

Test Category: CAN/UL Small

TEST PERFORMED: CAN/ULC-S109-14 * - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Small Flame Test

(* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

PRECONDITIONING:

☒ Standard method: 0.5 hour @ 105 ± 2°C☐ Alternate method for materials that are affected by heating to 105°C:☐ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by SGS Govmark): 275 g/m²

CONVERSION FACTORS:

mm ÷ 25.4 = inches

g/m² ÷ 28.35 x 0.0835 = oz/yd²

RESULTS ARE REPORTED:

☒ Initially

[code 215]

☐ After 10 dry cleanings

[code 435]

☐ After 10 launderings

[code 380]

☐ After 72 hours water leaching

[code 380]

☐ After scrubbing

[code 600]

☐ After 360 hours accelerated weathering

[code 5255]

Received: 09/06/2018		Completed: 09/07/2018		Letter: V	BG	P.O.#:	Test Report #: 3-28236-0-
Client's Identification		Style: Ultra Poplin Pes S240. Content: Polyester. End Use: Banner.					
Tested For: Kylie Schleicher Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869				Key Test: CAN/ULC-S109-14 Small Flame Test 195 Tel: 1-(973)-627-8608 Ext: Fax: 1-()- -			

RESULTS:	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Damaged Length (mm)
	-----	-----	-----	-----
Length:	1	0.0	0	100
	2	0.0	0	100
	3	0.0	0	135
	4	26.9	0	115
	5	0.0	0	135
Width:	6	0.0	0	130
	7	12.8	0	115
	8	0.0	0	115
	9	0.0	0	110
	10	0.0	0	130

			Avg:	119

REMARKS: None.


ACCEPTANCE CRITERIA:	Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
	-----	-----	-----
Maximum Average:	**	Not specified	165 mm (6.5")
Maximum Individual Specimen:	**	2.0	190 mm (7.5")

(** Surface Flaming values are required to be reported after removal of the 12 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

☒ Complies; ☐ Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



AUTHORIZED SIGNATURE
SGS GOVMARK
/jab

Phyllis Pettit
SEP 17 2018