

100% PVC-free / phthalate-free, waterproof substrate ideal for a wide range of outdoor applications including banners, outdoor signage, and POS. This material has high opacity to reduce translucency and shadowing and can be welded or sewn. EcoVantage Supreme is compatible with solvent, eco-solvent, UV, Latex and screen printing and available in widths from 54" to 196".

### Material Details

| CHARACTERISTICS  |                              | METRIC               | ENGLISH                 |
|------------------|------------------------------|----------------------|-------------------------|
| Composition      | DIN 60001, ASTM D7641        | 100% Polyester       |                         |
| Total Weight     | DIN EN ISO 2286-2 ASTM D751  | 310 g/m <sup>2</sup> | 9.1 oz./yd <sup>2</sup> |
| Denier           | DIN EN ISO 2060, ASTM D 1907 | 1000 x 1000          |                         |
| Tensile Strength | DIN EN ISO 1421              | 2290 x 2180 N/5cm    | 263 x 251 lbs/in        |
| Tear Strength    | DIN 53363                    | 730 x 690 N          | 164 x 155 lbs           |
| Fire Resistance  | NFPA 701                     |                      |                         |

### Applications

|              | Indoor | Banner | Outdoor | POS | Retail Applications | Display Systems | Billboard |
|--------------|--------|--------|---------|-----|---------------------|-----------------|-----------|
| Applications | ■      | ■      | ■       | ■   | ■                   | ■               | ■         |

### Ink Printability

### Available Sizes

| Solvent | Eco Solvent | UV | Latex | Screen Printing | Dye Transfer | Dye Direct |
|---------|-------------|----|-------|-----------------|--------------|------------|
| ■       | ■           | ■  | ■     | ■               |              |            |

| Metric (m)             | English (inches)     |
|------------------------|----------------------|
| 1.37, 1.60, 3.20, 5.00 | 54", 63", 126", 196" |

The information on physical and chemical characteristics is based upon tests believed to be reliable. The values are intended only as a source of information. A legally binding guarantee of specific properties is not to be inferred from our specifications. They are given without guarantee and do not constitute a warranty. The purchaser should independently determine, prior to use, the suitability of the material for his/her specific purpose. (Data represents averages and is not intended for use as a specification.)