



96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-895
e-mail: testing@govmark.com

Page 1

Received: 05/17/2018	Completed: 05/21/2018	Letter: M	MB	P.O.#:	Test Report #: 3-26130-0-
Client's Identification	Style: DSS 12oz. Content: Polyester. End Use: Indoor Banner.				
Tested For: Kylie Schleicher Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869			Key Test: CAN/ULC-S109-14 Large Flame Test 395 Single Sheet Tel: 1-(973)-627-8608 Ext: Fax: 1-()- -		

LE: 20 14; V 09/15
Test Category: CAN/UL Large Flat
Specifier: CAN/UL NTR 04/16 /dl

TEST PERFORMED: CAN/ULC-S109-14 * - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Large Flame Test, Single Sheet Specimen

(* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

PRECONDITIONING:

- ☒ Standard method: 0.5 hour @ 105 ± 2°C
- ☐ Alternate method for materials that are affected by heating to 105°C:
- ☐ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH
- ☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by Govmark): 432.5 g/m²

CONVERSION FACTORS:

mm ÷ 25.4 = inches
g/m² ÷ 28.35 x 0.0835 = oz/yd²

RESULTS ARE REPORTED:

- | | |
|---|-------------|
| <input checked="" type="checkbox"/> Initially | [code 395] |
| <input type="checkbox"/> After 10 dry cleanings | [code 595] |
| <input type="checkbox"/> After 10 launderings | [code 545] |
| <input type="checkbox"/> After 72 hours water leaching | [code 545] |
| <input type="checkbox"/> After scrubbing | [code 745] |
| <input type="checkbox"/> After 360 hours accelerated weathering | [code 5995] |



96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Page 2

Received: 05/17/2018 Completed: 05/21/2018 Letter: M MB P.O.#: Test Report #: 3-26130-0-

Client's Identification Style: DSS 12oz. Content: Polyester. End Use: Indoor Banner.

Tested For: **Kylie Schleicher**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: CAN/ULC-S109-14 Large Flame Test 395
Single Sheet
Tel: 1-(973)-627-8608 Ext:
Fax: 1-()- -

RESULTS:	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Damaged Length (mm)
Length:	1	0	0	32
	2	0	0	50
	3	0	0	52
	4	0	0	27
	5	0	0	45
Width:	6	0	0	12
	7	0	0	68
	8	0	0	25
	9	0	0	15
	10	0	0	75

REMARKS: None.


ACCEPTANCE CRITERIA:	Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
Maximum Average:	**	Not specified	Not specified
Maximum Individual Specimen:	**	2.0	250 mm

(** Surface Flaming values are required to be reported after removal of the 120 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

[x] Complies; [] Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



AUTHORIZED SIGNATURE

Phyllis Pettit

MAY 24 2018

SGS GOVMARK

/tm /pm

(Page 2 of 2)