

Received:05/21/2018	Completed:05/21/2018	Letter: V	BG	P.O.#:	Test Report #: 3-26184-0-
---------------------	----------------------	-----------	----	--------	---------------------------

Client's Identification	Style: Ultra Mesh Premium. Content: Polyester. End Use: Banner.
-------------------------	---

Tested For: Kylie Schleicher

Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: CAN/ULC-S109-14 Small Flame Test 195
Tel: 1-(973)-627-8608 Ext:
Fax: 1-()- -

LE 2014; V 09/15

Specifier: CAN/UL

NTR 04/16

/dl

Test Category: CAN/UL Small

TEST PERFORMED: CAN/ULC-S109-14 * - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Small Flame Test

(* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

PRECONDITIONING:
☒ Standard method: 0.5 hour @ 105 ± 2°C

☐ Alternate method for materials that are affected by heating to 105°C:

☐ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH

☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by Govmark): 348 g/m²

CONVERSION FACTORS:

mm ÷ 25.4 = inches

g/m² ÷ 28.35 x 0.0835 = oz/yd²

RESULTS ARE REPORTED:

<input checked="" type="checkbox"/> Initially	[code 195]
<input type="checkbox"/> After 10 dry cleanings	[code 395]
<input type="checkbox"/> After 10 launderings	[code 345]
<input type="checkbox"/> After 72 hours water leaching	[code 345]
<input type="checkbox"/> After scrubbing	[code 545]
<input type="checkbox"/> After 360 hours accelerated weathering	[code 4775]



96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Page 2

Received: 05/21/2018	Completed: 05/21/2018	Letter: V	BG	P.O.#:	Test Report #: 3-26184-0-
Client's Identification	Style: Ultra Mesh Premium. Content: Polyester. End Use: Banner.				
Tested For: Kylie Schleicher Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869			Key Test: CAN/ULC-S109-14 Small Flame Test 195 Tel: 1-(973)-627-8608 Ext: Fax: 1-()- -		

RESULTS:	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Damaged Length (mm)
	-----	-----	-----	-----
Length:	1	0	0	105
	2	0	0	130
	3	0	0	135
	4	0	0	155
	5	0	0	140
Width:	6	0	0	130
	7	0	0	133
	8	0	0	110
	9	0	0	145
	10	0	0	160

			Avg:	134

REMARKS: None.


ACCEPTANCE CRITERIA:	Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
	-----	-----	-----
Maximum Average:	**	Not specified	165 mm (6.5")
Maximum Individual Specimen:	**	2.0	190 mm (7.5")

(** Surface Flaming values are required to be reported after removal of the 12 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

☒ Complies; ☐ Does not comply


CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



AUTHORIZED SIGNATURE
SGS GOVMARK

Phyllis Pettit

MAY 29 2018

/mg 

(Page 2 of 2)

96-D Allen Boulevard
Farmingdale, New York 11735-5t
Tel. +1 (631) 293-8944 Fax +1 (6
e-mail: testing@govmark.com

Page

Received: 05/21/2018		Completed: 05/23/2018		Letter: V1	MB	P.O.#:	Test Report #:
Client's Identification		Style: Ultra Mesh Premium. Content: Polyester. End Use: Banner.					
Tested For = Kylie Schleicher							
Ultraflex Systems Inc.							
1578 Sussex Tpk., Bldg. #4							
Randolph, NJ 07869							
		Key Test: CAN/ULC-S109-14 Large Flame Test					
		Single Sheet					
		Tel: 1-(973)-627-8608				Ext:	
		Fax: 1-()- -					

LE: 2014; ✓ 09/15

Test Category: CAN/UL Large Flat

Specifier: CAN/UL

NTR 04/16

/dl

TEST PERFORMED: CAN/ULC-S109-14 * - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Large Flame Test, Single Sheet Specimen

(* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

PRECONDITIONING:

☒ Standard method: 0.5 hour @ 105 ± 2°C

☐ Alternate method for materials that are affected by heating to 105°C:

☐ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH

☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by Govmark): 348 g/m²

CONVERSION FACTORS:

mm ÷ 25.4 = inches

g/m² ÷ 28.35 x 0.0835 = oz/yd²

RESULTS ARE REPORTED:

- ☒ Initially
- ☐ After 10 dry cleanings
- ☐ After 10 launderings
- ☐ After 72 hours water leaching
- ☐ After scrubbing
- ☐ After 360 hours accelerated weathering

[code 395]
[code 595]
[code 545]
[code 545]
[code 745]
[code 5995]