



96-D Allen Boulevard  
Farmingdale, New York 11735-5626 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
e-mail: testing@govmark.com

Page 1

Received: 05/17/2018	Completed: 05/21/2018	Letter: R	MB	P.O.#:	Test Report #:	3-26135-0-
----------------------	-----------------------	-----------	----	--------	----------------	------------

Client's Identification	Style: Ultra Mesh Supreme. Content: Polyester. End Use: Banners.
-------------------------	--

Tested For: <b>Kylie Schleicher</b> Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869	Key Test: CAN/ULC-S109-14 Large Flame Test 395 Single Sheet Tel: 1-(973)-627-8608 Ext: Fax: 1-( )- -
---	---

LE: 2014; V 09/15                      Specifier: CAN/UL                      NTR 04/16                      /dl  
Test Category: CAN/UL Large Flat

TEST PERFORMED: CAN/ULC-S109-14 \* - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Large Flame Test, Single Sheet Specimen

(\* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

PRECONDITIONING:

☒ Standard method: 0.5 hour @ 105 ± 2°C

☐ Alternate method for materials that are affected by heating to 105°C:

☐ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH

☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by Govmark): 321.0 g/m<sup>2</sup>

CONVERSION FACTORS:

mm ÷ 25.4 = inches

g/m<sup>2</sup> ÷ 28.35 x 0.0835 = oz/yd<sup>2</sup>

RESULTS ARE REPORTED:

<input checked="" type="checkbox"/> Initially	[code 395]
<input type="checkbox"/> After 10 dry cleanings	[code 595]
<input type="checkbox"/> After 10 launderings	[code 545]
<input type="checkbox"/> After 72 hours water leaching	[code 545]
<input type="checkbox"/> After scrubbing	[code 745]
<input type="checkbox"/> After 360 hours accelerated weathering	[code 5995]



96-D Allen Boulevard  
Farmingdale, New York 11735-5626 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
e-mail: testing@govmark.com

Page 2

Received:05/17/2018 Completed:05/21/2018 Letter: R MB P.O.#: Test Report #: 3-26135-0-

Client's Identification Style: Ultra Mesh Supreme. Content: Polyester. End Use: Banners.

Tested For: **Kylie Schleicher**

Ultraflex Systems Inc.  
1578 Sussex Tpk., Bldg. #4  
Randolph, NJ 07869

Key Test: CAN/ULC-S109-14 Large Flame Test 395

Single Sheet

Tel: 1-(973)-627-8608

Ext:

Fax: 1-( )- -

RESULTS:	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Damaged Length (mm)
Length:	1	0	0	48
	2	0	0	86
	3	0	0	36
	4	0	0	70
	5	0	0	97
Width:	6	0	0	66
	7	0	0	71
	8	0	0	88
	9	0	0	40
	10	0	0	24

REMARKS: None.

ACCEPTANCE CRITERIA:	Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
Maximum Average:	**	Not specified	Not specified
Maximum Individual Specimen:	**	2.0	250 mm

(\*\* Surface Flaming values are required to be reported after removal of the 120 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

☒ Complies; ☐ Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

Phyllis Pettit

AUTHORIZED SIGNATURE

SGS GOVMARK

/tm /pm

MAY 24 2018

(Page 2 of 2)