

TEST REPORT

APPLICANT : ULTRAFLEX SYSTEMS INC.

REPORT NO. : M216-12-04377

SAMPLE RECEIVED DATE : 2012-07-05

TEST STARTED DATE : 2012-07-05

REPORT ISSUED DATE : 2012-07-11

PAGE : 1 OF 2

SAMPLE DESCRIPTION : ONE(1) PIECE OF SUBMITTED CUTTING SAID TO BE COATED FABRIC.

ITEM : BILLBOARD 520

TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGES.

PREPARED AND CHECKED BY
FOR FITI

YOUN SOO SHIN

YOUN SOO, SHIN
QUALITY MANAGER

AUTHORIZED BY
FOR FITI

MOON OK NOH

MOON-OK NOH
PRESIDENT

REPORT NO. : M216-12-04377
PAGE : 2 OF 2

TEST CONDUCTED

TEST RESULT

(01) FLAMMABILITY (NFPA 701 TEST METHOD 1(2010))

#1

SAMPLE NO.	WEIGHT(g)		WEIGHT LOSS(%)	AFTER FLAME TIME(s)	DRIP BURN(s)
	ORIGINAL	AFTER TEST			
1	13.4	13.2	1.5	0.0	0.0
2	12.9	12.5	3.1	0.0	0.0
3	13.0	12.8	1.5	0.0	0.0
4	13.2	12.6	4.5	0.0	0.0
5	13.1	12.4	5.3	0.0	0.0
6	13.0	12.7	2.3	0.0	0.0
7	13.2	12.6	4.5	0.0	0.0
8	13.1	12.5	4.6	0.0	0.0
9	13.3	12.4	6.8	0.0	0.0
10	12.9	12.8	0.8	0.0	0.0
AVG.	13.1	12.7	3.5	0.0	0.0

NOTE) • CONCLUSION : BASED UPON THE RESULTS OF THE TEST REPORT, THE SUBMITTED SAMPLE MEETS THE PERFORMANCE REQUIREMENT AS STATED IN NFPA 701 TEST METHOD 1(2010).

• PERFORMANCE CRITERIA FOR TEST 1

DRIP BURN(s)	WEIGHT LOSS(%)	NO INDIVIDUAL SPECIMEN'S WEIGHT LOSS EXCEED THE MEAN VALUE PLUS 3 STANDARD DEVIATION 9.4 (STANDARD DEVIATION = 1.95
AVG. : LESS THAN 2	AVG. : LESS THAN 40	

• TEST WAS CONDUCTED ONLY IN THE ORIGINAL STATE BY THE CLIENT'S REQUEST.

SAMPLE :