



GOVMARK

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
email: govmark.accounting@sgs.com

Page 1

Received:09/06/2018	Completed:09/10/2018	Letter: W1	AM	P.O.#:	Test Report #:	3-28237-1-
---------------------	----------------------	------------	----	--------	----------------	------------

Client's Identification	Style: Pole Banner. Content: Polyester. End Use: Banner.
-------------------------	--

Tested For: Kylie Schleicher Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869	Key Test: CAN/ULC-S109-14 Large Flame Test 395 Single Sheet Tel: 1-(973)-627-8608 Fax: 1-()- -	Ext:
---	--	------

LE: 2014; V 09/18 Specifier: CAN/UL NTR 04/16 /dl
Test Category: CAN/UL Large Flat

TEST PERFORMED: CAN/ULC-S109-14 * - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Large Flame Test, Single Sheet Specimen

(* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

PRECONDITIONING:

☒ Standard method: 0.5 hour @ 105 ± 2°C

☐ Alternate method for materials that are affected by heating to 105°C:

☐ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH

☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by SGS Govmark): 656 g/m²

CONVERSION FACTORS:

mm ÷ 25.4 = inches

g/m² ÷ 28.35 x 0.0835 = oz/yd²

RESULTS ARE REPORTED:

<input checked="" type="checkbox"/> Initially	[code 435]
<input type="checkbox"/> After 10 dry cleanings	[code 655]
<input type="checkbox"/> After 10 launderings	[code 600]
<input type="checkbox"/> After 72 hours water leaching	[code 600]
<input type="checkbox"/> After scrubbing	[code 820]
<input type="checkbox"/> After 360 hours accelerated weathering	[code 6595]



GOVMARK

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
email: govmark.accounting@sgs.com

Page 2

Received:09/06/2018 Completed:09/10/2018 Letter: W1 AM P.O.#: Test Report #: 3-28237-1-

Client's Identification Style: Pole Banner. Content: Polyester. End Use: Banner.

Tested For: **Kylie Schleicher**
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: CAN/ULC-S109-14 Large Flame Test 395
Single Sheet
Tel: 1-(973)-627-8608 Ext:
Fax: 1-()- -

RESULTS:	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Damaged Length (mm)
Length:	1	0.0	0	30
	2	0.0	0	0
	3	0.0	0	12
	4	0.0	0	0
	5	29.0	0	10
Width:	6	0.0	0	0
	7	0.0	0	0
	8	13.0	0	20
	9	0.0	0	10
	10	0.0	0	0

REMARKS: None.

ACCEPTANCE CRITERIA:	Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
Maximum Average:	**	Not specified	Not specified
Maximum Individual Specimen:	**	2.0	250 mm

(** Surface Flaming values are required to be reported after removal of the 120 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

[x] Complies; [] Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

Phyllis Pettit

SEP 17 2018

AUTHORIZED SIGNATURE
SGS GOVMARK

/jab

(Page 2 of 2)