



Received: 04/22/2015	Completed: 04/24/2015	Letter: J	AM	P.O.#:	Test Report #:	3-07522-0-
Client's Identification	Style: Strip Mesh Pro LTX. Content: Polyester. End Use: Banner Material/Outdoor.					
Tested For: Kylie Schleicher Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869				Key Test: CAN/ULC-S109-14 Small Flame Test 195 Tel: 1-(973)-627-8608 Ext: Fax: 1-()- -		

Test Category: CAN/UL Small Specifier: CAN/UL /jd

TEST PERFORMED: CAN/ULC-S109-14 * - Standard for Flame Tests of Flame-Resistant Fabrics & Films, Small Flame Test

(* Note: This document was prepared and published by Underwriters' Laboratories of Canada and is approved as a National Standard of Canada.)

PRECONDITIONING:

☒ Standard method: 0.5 hour @ 105 ± 2°C

☐ Alternate method for materials that are affected by heating to 105°C:

☐ Desiccator method: 12 hours minimum @ 20 ± 2°C and 50 ± 5% RH

☐ Alternate oven method: 1 hour @ 60 ± 2°C

APPROXIMATE AREA DENSITY OF MATERIAL (as measured by Govmark): 394 gm/m²

CONVERSION FACTORS:

mm ÷ 25.4 = inches

g/m² ÷ 28.35 x 0.0835 = oz/yd²

RESULTS ARE REPORTED:

<input checked="" type="checkbox"/> Initially	[code 195]
<input type="checkbox"/> After 10 dry cleanings	[code 395]
<input type="checkbox"/> After 10 launderings	[code 345]
<input type="checkbox"/> After 72 hours water leaching	[code 345]
<input type="checkbox"/> After scrubbing	[code 545]
<input type="checkbox"/> After 360 hours accelerated weathering	[code 4775]

Received:04/22/2015	Completed:04/24/2015	Letter: J	AM	P.O.#:	Test Report #: 3-07522-0-
---------------------	----------------------	-----------	----	--------	---------------------------

Client's Identification	Style: Strip Mesh Pro LTX. Content: Polyester. End Use: Banner Material/Outdoor.
--------------------------------	--

Tested For: Kylie Schleicher Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869	Key Test: CAN/ULC-S109-14 Small Flame Test 195 Tel: 1-(973)-627-8608 Ext: Fax: 1-()- -
---	---

RESULTS:	Specimen #	Surface Flaming** (seconds)	Flaming Drip (seconds)	Damaged Length (mm)
Length:	1	0	0	120
	2	0	0	110
	3	0	0	129
	4	0	0	106
	5	0	0	146
Width:	6	0	0	110
	7	0	0	123
	8	0	0	143
	9	0	0	110
	10	0	0	106
			Avg:	120

REMARKS: None.


ACCEPTANCE CRITERIA:	Surface Flaming (seconds)	Flaming Drip (seconds)	Damaged Length
Maximum Average:	**	Not specified	165 mm (6.5")
Maximum Individual Specimen:	**	2.0	190 mm (7.5")

(** Surface Flaming values are required to be reported after removal of the 12 seconds igniting flame; however, these values are not required to be factored into determination of acceptance.)

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

☒ Complies; ☐ Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by CAN/ULC-S109-14.



 AUTHORIZED SIGNATURE
 GOVMARK
 /ec /tm

MS. PHYLLIS RETTIT
MAY 0 1 2015