



Received: 04/26/2010	Completed: 05/14/2010	Letter: P1	rb	P.O.#:	Test Report #: 2-83036-1-
Client's Identification	Style: Ultra Block Banner Pro. Content: Polyester. Finish: PVC. Weight: 15-20oz/yd <sup>2</sup> . End Use: In/Outdoor Signs & Banner.				
Tested For: <b>Jaime L. Giannantonio</b> Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869			Key Test: NFPA 701-2010 TM#2 Flat WL 490  Tel: 1-(973)-627-8608 Ext: 124 Fax: 1-(973)-627-8506		

PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2010 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: ☒ Single Layer; ☐ Multi Layer

RESULTS REPORTED: ☐ Initially ☒ After 72 hours water leaching  
☐ After 3 dry cleanings ☐ After 100 hours accelerated weathering  
☐ After 5 launderings @ 160°F

RESULTS:

Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	120
2	0	0	170
3	0	0	150
4	0	0	200
5	0	0	170
6	0	0	200
7	0	0	200
8	0	0	140
9	0	0	160
10	0	0	90

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 543 g/m<sup>2</sup>

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

☒ Passes; ☐ Fails; ☐ Requires testing of 5 additional specimens

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2010 Edition Test Method #2 Flat Sheet Specimens.

*Heather S. Robertson*

AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC. / ec / mg (Page 1 of 2)

MS. HEATHER ROBERTSON JUN 04 2010



<b>Received:</b> 04/26/2010		<b>Completed:</b> 05/14/2010		<b>Letter:</b> P1	rb	<b>P.O.#:</b>	<b>Test Report #:</b> 2-83036-1-
<b>Client's Identification</b>	Style: Ultra Block Banner Pro. Content: Polyester. Finish: PVC. Weight: 15-20oz/yd <sup>2</sup> . End Use: In/Outdoor Signs & Banner.						
<b>Tested For:</b> Jaime L. Giannantonio Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869				<b>Key Test:</b> NFPA 701-2010 TM#2 Flat WL 490  <b>Tel:</b> 1-(973)-627-8608 <b>Ext:</b> 124 <b>Fax:</b> 1-(973)-627-8506			

PRECONDITIONING:    ☒ 1 hr @ 220°F (Standard)  
                             ☐ 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS:  
None.

CONVERSION FACTORS:  
mm ÷ 25.4 = inches  
g/m<sup>2</sup> ÷ 28.35 x .835 = oz/yd<sup>2</sup>

(Page 2 of 2)