



The
Govmark
Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Page 1

Received: 02/21/2012 Completed: 02/27/2012 Letter: H rb P.O.#: Test Report #: 2-91109-0-

Client's Identification Style: DSS Pro 14oz Blockout. Content: Polyester. Weight: 14oz. End Use: Blockout Sign Material.

Tested For: **Jaime Sherman** Key Test: NFPA 701-2010 TM#2 Flat 340
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4 Tel: 1-(973)-627-8608 Ext:
Randolph, NJ 07869 Fax: 1-(973)-627-8506

PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films
- 2010 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: ☒ Single Layer; ☐ Multi Layer

RESULTS REPORTED: ☒ Initially ☐ After 72 hours water leaching
☐ After 3 dry cleanings ☐ After 100 hours accelerated weathering
☐ After 5 launderings @ 160°F

RESULTS:

Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	245
2	0	0	170
3	0	0	162
4	0	0	175
5	0	0	183
6	0	0	197
7	0	0	152
8	0	0	175
9	0	0	183
10	0	0	165

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 460 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

☒ Passes; ☐ Fails; ☐ Requires testing of 5 additional specimens

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2010 Edition Test Method #2 Flat Sheet Specimens.

MAR 13 2012

AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC. /rb /mg

(Page 1 of 2)

MS. PHYLLIS PETTIT

File Copy



The
Govmark
Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Page 2

Received: 02/21/2012	Completed: 02/27/2012	Letter: H	rb	P.O.#:	Test Report #:	2-91109-0-
Client's Identification	Style: DSS Pro 14oz Blockout. Content: Polyester. Weight: 14oz. End Use: Blockout Sign Material.					
Tested For: Jaime Sherman Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869			Key Test: NFPA 701-2010 TM#2 Flat			340
			Tel: 1-(973)-627-8608		Ext:	
			Fax: 1-(973)-627-8506			

PRECONDITIONING: ☒ 1 hr @ 220°F (Standard)
 ☐ 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS: Client requested that the restraining clamp binder clips be eliminated to replicate the provisions of the 1996 Test Method #1 version of this document.

CONVERSION FACTORS:
mm ÷ 25.4 = inches
g/m² ÷ 28.35 x .835 = oz/yd²

(Page 2 of 2)



The
Govmark
Organization, Inc.

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Page 1

Received:02/21/2012 Completed:03/02/2012 Letter: H1 rb P.O.#: Test Report #: 2-91109-1-

Client's Identification Style: DSS Pro 14oz Blockout. Content: Polyester. Weight: 14oz. End Use: Blockout Sign Material.

Tested For: **Jaime Sherman** Key Test: NFPA 701-2010 TM#2 Flat WL 490
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869
Tel: 1-(973)-627-8608 Ext:
Fax: 1-(973)-627-8506

PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films
- 2010 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: ☒ Single Layer; ☐ Multi Layer

RESULTS REPORTED: ☐ Initially ☒ After 72 hours water leaching
☐ After 3 dry cleanings ☐ After 100 hours accelerated weathering
☐ After 5 launderings @ 160°F

RESULTS:

Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	150
2	0	0	147
3	0	0	130
4	0	0	117
5	0	0	120
6	0	0	133
7	0	0	129
8	0	0	119
9	0	0	141
10	0	0	156

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 460 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

☒ Passes; ☐ Fails; ☐ Requires testing of 5 additional specimens

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2010 Edition Test Method #2 Flat Sheet Specimens.

AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC. /rb /mg

MAR 13 2012

(Page 1 of 2)

MS. PHYLLIS PETTIT

File Copy



Received: 02/21/2012	Completed: 03/02/2012	Letter: H1	rb	P.O.#:	Test Report #:	2-91109-1-
----------------------	-----------------------	------------	----	--------	----------------	------------

Client's Identification	Style: DSS Pro 14oz Blockout. Content: Polyester. Weight: 14oz. End Use: Blockout Sign Material.
-------------------------	--

Tested For: Jalme Sherman Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869	Key Test: NFPA 701-2010 TM#2 Flat WL 490 Tel: 1-(973)-627-8608 Ext: Fax: 1-(973)-627-8506
--	---

PRECONDITIONING: ☒ 1 hr @ 220°F (Standard)
 ☐ 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS: Client requested that the restraining clamp binder clips be eliminated to replicate the provisions of the 1996 Test Method #1 version of this document.

CONVERSION FACTORS:
mm ÷ 25.4 = inches
g/m² ÷ 28.35 x .835 = oz/yd²

(Page 2 of 2)