



GOVMARK

96-D Allen Boulevard  
Farmingdale, New York 11735-5626 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
email: govmark.accounting@sgs.com

Page 1

<b>Received:</b> 08/27/2018		<b>Completed:</b> 08/28/2018		<b>Letter:</b> M	RM	<b>P.O.#:</b>	<b>Test Report #:</b> 3-28048-0-
<b>Client's Identification</b>		Style: ProFlex. Composition: Polyester. Product End Use: Banners.					
<b>Tested For:</b> <b>Kylie Schleicher</b> Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869				<b>Key Test:</b> NFPA 701-2015 TM#2 Flat 475  <b>Tel:</b> 1-(973)-627-8608 <b>Ext:</b> <b>Fax:</b> 1-( )- -			

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2015 Edition - Test Method #2 - Flat Sheet Specimens

PC:1H

SPECIMEN CONFIGURATION: ☒ Single Layer; ☐ Multi Layer

RESULTS REPORTED: ☒ Initially ☐ After 72 hours water leaching  
☐ After 3 dry cleanings ☐ After 100 hours accelerated weathering  
☐ After 5 launderings @ 160°F

## RESULTS:

Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	312
2	0	0	258
3	0	0	362
4	0	0	326
5	0	0	297
6	0	0	301
7	0	0	334
8	0	0	281
9	0	0	267
10	0	0	299

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 424 g/m<sup>2</sup>

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

☒ Passes; ☐ Fails; ☐ Requires testing of 5 additional specimens

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2015 Edition Test Method #2 Flat Sheet Specimens.

Phyllis Pettit

SEP 05 2018

AUTHORIZED SIGNATURE

SGS GOVMARK

/jab /jb

(Page 1 of 2)



GOVMARK

96-D Allen Boulevard  
Farmingdale, New York 11735-5626 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
email: govmark.accounting@sgs.com

Page 2

Received:08/27/2018	Completed:08/28/2018	Letter: M	RM	P.O.#:	Test Report #: 3-28048-0-
Client's Identification	Style: ProFlex. Composition: Polyester. Product End Use: Banners.				
Tested For: <b>Kylie Schleicher</b> Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869			Key Test: NFPA 701-2015 TM#2 Flat 475 Tel: 1-(973)-627-8608 Ext: Fax: 1-( )- -		

PRECONDITIONING: ☒ 1 hr @ 220°F (Standard)  
☐ 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS: Client requested that the restraining clamp binder clips be eliminated to replicate the provisions of the 1996 Test Method #1 version of this document.

CONVERSION FACTORS:  
mm ÷ 25.4 = inches  
g/m<sup>2</sup> ÷ 28.35 x .835 = oz/yd<sup>2</sup>

(Page 2 of 2)