

Received: 11/20/2019	Completed: 11/21/2019	Letter: S	JR	P.O.#:	Test Report #: 3-35688-0-
Client's Identification	Style: Ultramash Eclipse. Composition: Polyester. Product End Use: Banners/Signage.				
Tested For: Kylie Schleicher Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869			Key Test: NFPA 701-2019 TM#2 Flat 525 Tel: 1-(973)-627-8608 Ext: Fax: 1-()- -		

LE:2019 NE:2021 V:12/18 NTR 04/16 PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2019 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: ☒ Single Layer; ☐ Multi Layer

RESULTS REPORTED: ☒ Initially ☐ After 72 hours water leaching
☐ After 3 dry cleanings ☐ After 100 hours accelerated weathering
☐ After 5 launderings @ 160°F

RESULTS: Length Specimen #	Afterflame (seconds)	Flaming Drip/Debris (seconds)	Char Length (mm)
-----	-----	-----	-----
1	0	0	231
2	0	0	212
3	0	0	183
4	0	0	199
5	0	0	226
6	0	0	219
7	0	0	195
8	0	0	166
9	0	0	132
10	0	0	248

APPROXIMATE WEIGHT OF MATERIAL (as measured by SGS Govmark): 272 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip/Debris Burn	Char Length
-----	-----	-----
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

☒ Passes; ☐ Fails; ☐ Requires testing of 5 additional specimens

Received: 11/20/2019	Completed: 11/21/2019	Letter: S	JR	P.O.#:	Test Report #:	3-35688-0-
Client's Identification	Style: Ultramesh Eclipse. Composition: Polyester. Product End Use: Banners/Signage.					
Tested For: Kylie Schleicher			Key Test: NFPA 701-2019 TM#2 Flat			525
Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869			Tel: 1-(973)-627-8608			Ext:
			Fax: 1-()- -			

PRECONDITIONING: ☒ 1 hr @ 220°F (Standard)
 ☐ 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS: Client requested that the restraining clamps be eliminated to replicate the provisions of the 1996 Test Method #1 version of this document.

CONVERSION FACTORS:

mm ÷ 25.4 = inches
g/m² ÷ 28.35 x .835 = oz/yd²

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED SIGNATURE

SGS GOVMARK

/jab /pm

Bobby Brown

(Page 2 of 2)

NOV 27 2019