



GOVMARK

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
email: govmark.accounting@sgs.com

Received:06/07/2019 Completed:06/10/2019 Letter: E1 JR P.O.#: Test Report #: 3-32879-1-

Client's Identification Style: ProFlex Smooth Banner. Composition: Polyester. Product End Use: Banners.

Tested For: **Kylie Schleicher** Key Test: NFPA 701-2019 TM#2 Flat 525
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869
Tel: 1-(973)-627-8608 Ext:
Fax: 1-()- -

LE:2019 NE:2021 V:12/18 NTR 04/16 PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2019 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: Single Layer; Multi Layer

RESULTS REPORTED: Initially After 72 hours water leaching
 After 3 dry cleanings After 100 hours accelerated weathering
 After 5 launderings @ 160°F

RESULTS: Length Specimen #	Afterflame (seconds)	Flaming Drip/Debris (seconds)	Char Length (mm)
1	0	0	153
2	0	0	166
3	0	0	161
4	0	0	158
5	0	0	191
6	0	0	172
7	0	0	165
8	0	0	169
9	0	0	158
10	0	0	156

APPROXIMATE WEIGHT OF MATERIAL (as measured by SGS Govmark): 340 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip/Debris Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

Passes; Fails; Requires testing of 5 additional specimens



GOVMARK

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
email: govmark.accounting@sgs.com

Received: 06/07/2019 Completed: 06/10/2019 Letter: E1 JR P.O.#: Test Report #: 3-32879-1-

Client's Identification Style: ProFlex Smooth Banner. Composition: Polyester. Product End Use: Banners.

Tested For: **Kylie Schleicher** Key Test: NFPA 701-2019 TM#2 Flat 525
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4 Tel: 1-(973)-627-8608 Ext:
Randolph, NJ 07869 Fax: 1-()- -

PRECONDITIONING: [x] 1 hr @ 220°F (Standard)
[] 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS: Client requested that the restraining clamps be eliminated to replicate the provisions of the 1996 Test Method #1 version of this document.

CONVERSION FACTORS:

mm ÷ 25.4 = inches
g/m² ÷ 28.35 x .835 = oz/yd²

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED SIGNATURE
SGS GOVMARK
/mg /pm

Bobby Brown
JUN 25 2019