

Page 1

Received:02/0	1/2010 Completed: 02/05/2010	Letter: A3	rb	P.O.#:	Test Report #:	2-82019-0-
Client's Identification	Super Print Plus Eclipse Black-	Backed Economy	Fron	t-Lit Banner Vinyl. Polyes	ter Weight: 13 oz.	Finish: Matte & Gloss.
	aime L. Giannantonio Itraflex Systems Inc.			Key Test: CA	1237 Sm	115
	578 Sussex Tpk., Bldg. #4 andolph, NJ 07869			•	973)-627-8608 973)-627-8506	Ext: 124

PC: 1H /id

Fax: 1-(973)-627-8506

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - EXTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED:

[x] Initially

[ ] After 72 hours water leaching

[ ] After 100 hours weathering

RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)
Warp:	1	0	0	3.9
	2	0	0	5.0
	3	0	0	4.0
	4	0	0	3.8
	5	0	0	4.3
	rA.	7g: 0		
Fill:	6	0	0	4.2
	7	0	0	4.8
	8	0	0	5.3
1	9	0	0	4.8
	10	0	0	5.2
	Avç	g: 0		

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 13.5 oz/yd²

# ACCEPTANCE CRITERIA:

Afterflame: 4.0 seconds maximum avg for length or width

Afterglow:

(see Note #2 below)

Char Length: 6.0" maximum for any individual specimen

# Notes:

- 1. An asterisk (\*) next to any char length measurements indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd2.
- 2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.

(Page 1 of 2)



Page 2

Received: 02/01/2010 Completed: 02/05/2010 Letter: A3 rb P.O.#: Test Report #: 2-82019-0-Client's Super Print Plus Eclipse Black-Backed Economy Front-Lit Banner Vinyl. Polyester Weight: 13 oz. Finish: Matte & Gloss. Identification Tested For: Jaime L. Giannantonio Key Test: CA 1237 Sm 115 Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Tel: 1-(973)-627-8608 Ext: 124 Randolph, NJ 07869 Fax: 1-(973)-627-8506

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

[x] Complies; [ ] Does not comply

REMARKS: None.

NOTE: In August 1993 the State Fire Marshal issued a proposed revision, which permitted a maximum average afterflame of 4.0 seconds. This proposed revision was honored by the subsequent State Fire Marshal until approximately February 2004, at which time the State Fire Marshal's office reverted to the unrevised rule of 2.0 seconds maximum average for exterior fabric.

In a conversation with the latest California State Fire Marshal on August 9, 2007, it was learned that the proposed 1993 revision is now back in effect. In addition to allowing 4 seconds Afterflame rather than 2 seconds, the proposed revision provides for testing of 10 specimens, rather than 6 specimens. This information has been verified current per an August 26, 2009 conversation with the California State Fire Marshall.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93).

AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC. / ec/max

MS. HEATHER ROBERTSON

FEB 1 9 2010

(Page 2 of 2)



Page 1

Received:02/0	1/2010	Completed: 02/16/2010	Letter: A4	rb	P.O.#:	Test Report #:	2-82019-1-
Client's Identification	Super	Print Plus Eclipse Black-	Backed Economy	y Fron	t-Lit Banner Vinyl.	Polyester Weight: 13 oz. F	Finish: Matte & Gloss.
		L. Giannantonio x Systems Inc.			Key Tes	t: CA 1237 Sm WL	115
		ssex Tpk., Bldg. #4 h, NJ 07869				l: 1-(973)-627-8608 x: 1-(973)-627-8506	Ext: 124

PC: 1H /jd

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - EXTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED:

[ ] Initially

[x] After 72 hours water leaching

[ ] After 100 hours weathering

RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)
Warp:	1	0	0	3.8
	2	0	0	5.1
	3	0	0	4.0
	4	0	0	3.7
	5	0	0	4.3
	Avg:	0		
Fill:	6	0	0	3.6
	7	0	0	4.5
	8	0	0	4.6
	9	0	0	4.1
	10	0	0	2.9
	Avq:	0		

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 13.5 oz/yd²

### ACCEPTANCE CRITERIA:

Afterflame: 4.0 seconds maximum avg for length or width

Afterglow: (see Note #2 below)

Char Length: 6.0" maximum for any individual specimen

### Notes:

- 1. An asterisk (\*) next to any char length measurements indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd².
- 2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.

(Page 1 of 2)



Page 2

Received:02/0	01/2010 Completed: 02/16/2010	Letter: A4	rb	P.O.#:	Test Report #:	2-82019-1-
Client's Identification	Super Print Plus Eclipse Black-	Backed Econo	my Fron	nt-Lit Banner Viny	l. Polyester Weight: 13 oz.	Finish: Matte & Gloss.
	Jaime L. Giannantonio Ultraflex Systems Inc.		•	Кеу Т	Cest: CA 1237 Sm WL	115
,	1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869				Tel: 1-(973)-627-8608 Pax: 1-(973)-627-8506	Ext: 124

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

[x] Complies; [ ] Does not comply

REMARKS: None.

NOTE: In August 1993 the State Fire Marshal issued a proposed revision, which permitted a maximum average afterflame of 4.0 seconds. This proposed revision was honored by the subsequent State Fire Marshal until approximately February 2004, at which time the State Fire Marshal's office reverted to the unrevised rule of 2.0 seconds maximum average for exterior fabric.

In a conversation with the latest California State Fire Marshal on August 9, 2007, it was learned that the proposed 1993 revision is now back in effect. In addition to allowing 4 seconds Afterflame rather than 2 seconds, the proposed revision provides for testing of 10 specimens, rather than 6 specimens. This information has been verified current per an August 26, 2009 conversation with the California State Fire Marshall.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93).

AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC. / ec/

MS. HEATHER ROBERTSON

FEB 1 9 2010

(Page 2 of 2)



Randolph, NJ 07869

96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 e-mail: info@govmark.com

Page 1

Received:02/0	1/2010 Completed: 02/16/2010	Letter: A5	rb	P.O.#:	Test Report #:	2-82019-2-
Client's Identification	Super Print Plus Eclipse Black	-Backed Economy	y Fron	t-Lit Banner Vinyl. Polyester	r Weight: 13 oz. Fi	nish: Matte & Gloss.
Tested For: J	aime L. Giannantonio			Key Test: CA 12	237 Sm AW	115
1	Iltraflex Systems Inc. 578 Sussex Tpk., Bldg. #4			<b>Tel: 1-(97</b> )	3)-627-8608	Ext: 124

PC: 1H /jd

Fax: 1-(973)-627-8506

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - EXTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED:

[ ] Initially

[ ] After 72 hours water leaching [x] After 100 hours weathering

RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)
Warn.	1	0	0	4.1
Warp:	<del>-</del>	0	-	
	2	Ü	0	4.0
	3	0	0	4.2
	4	0	0	3.7
	5	0	0	5.1
		Avg: 0		
Fill:	6	0	0	4.6
	7	0	0	4.4
	8	0	0	5.4
ļ	9	0	0	3.8
	10	0	0	3.9
	P	Avg: 0		

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 13.5 oz/yd²

#### ACCEPTANCE CRITERIA:

Afterflame: 4.0 seconds maximum avg for length or width

Afterglow: (see Note #2 below)

Char Length: 6.0" maximum for any individual specimen

#### Notes:

- 1. An asterisk (\*) next to any char length measurements indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd².
- 2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.

(Page 1 of 2)



Page 2

Received:02	/01/2010 <b>C</b>	Completed: 02/16/2010	Letter: A5	rb	P.O.#:	Test Report #:	2-82019-2-
Client's Identification		rint Plus Eclipse Black-	Backed Econor	my Fron	nt-Lit Banner Ving	yl. Polyester Weight: 13 oz. Fi	nish: Matte & Gloss.
Tested For:		. <b>Giannantonio</b> Systems Inc.			Key 7	Test: CA 1237 Sm AW	115
	1578 Suss	sex Tpk., Bldg. #4 , NJ 07869				Tel: 1-(973)-627-8608 Fax: 1-(973)-627-8506	Ext: 124

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

[x] Complies; [ ] Does not comply

REMARKS: None.

NOTE: In August 1993 the State Fire Marshal issued a proposed revision, which permitted a maximum average afterflame of 4.0 seconds. This proposed revision was honored by the subsequent State Fire Marshal until approximately February 2004, at which time the State Fire Marshal's office reverted to the unrevised rule of 2.0 seconds maximum average for exterior fabric.

In a conversation with the latest California State Fire Marshal on August 9, 2007, it was learned that the proposed 1993 revision is now back in effect. In addition to allowing 4 seconds Afterflame rather than 2 seconds, the proposed revision provides for testing of 10 specimens, rather than 6 specimens. This information has been verified current per an August 26, 2009 conversation with the California State Fire Marshall.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93).

AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC. / ec/ $\gamma\gamma\gamma$ 

MS. HEATHER ROBERTSON

FEB 1 9 2010

(Page 2 of 2)