



96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Page 1

Received: 05/13/2015 Completed: 05/14/2015 Letter: F JS P.O.#: Test Report #: 3-07900-0-

Client's Identification Style: SuperPrint Smooth Banner. Composition: Polyester/PVC. Product End Use: Indoor Banners.

Tested For: Kylie Schleicher

Key Test: CA 1237 Sm

175

Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Tel: 1-(973)-627-8608 Ext:
Fax: 1-()- -

PC: 1H /jd SM/mg

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - INTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED: [x] Initially
[] After 3 dry cleanings
[] After 5 launderings @ 160°F

RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)
Warp:	1	0	0	4.5
	2	0	0	4.7
	3	0	0	3.9
	4	0	0	3.8
	5	0	0	3.9
	Avg:	0		
Fill:	6	0	0	4.1
	7	0	0	3.9
	8	0	0	4.2
	9	0	0	4.3
	10	0	0	5.6
	Avg:	0		

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 10.2 oz/yd²

ACCEPTANCE CRITERIA:

Afterflame: 4.0 seconds maximum average for warp or fill
Afterglow: (see Note #2 below)
Char Length: 6.0 inches maximum for any individual specimen

NOTES:

1. An asterisk (*) next to any char length measurement indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd².
2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.

(Page 1 of 2)

File Copy



96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Page 2

Received: 05/13/2015	Completed: 05/14/2015	Letter: F	JS	P.O.#:	Test Report #:	3-07900-0-
Client's Identification	Style: SuperPrint Smooth Banner. Composition: Polyester/PVC. Product End Use: Indoor Banners.					
Tested For: Kylie Schleicher Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869			Key Test: CA 1237 Sm			175
			Tel: 1-(973)-627-8608			Ext:
			Fax: 1-() - -			

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

☒ Complies; ☐ Does not comply

REMARKS: None.

NOTE: The number of test specimens and Acceptance Criteria are based on a proposed revision issued and implemented by the California State Fire Marshal in August 1993. In substance, the following has occurred:

1. A maximum afterflame of 4 seconds is permitted as opposed to 1 second.
2. It was clarified that the char length maximum of 6 inches applies to any individual specimen and is not an average requirement.
3. Ten specimens are tested in lieu of 6 specimens.

This report issues the conclusion to Section 1237 based on the California State Fire Marshal's continued endorsement of the proposed revision.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Fire Marshal Title 19: Section 1237 Small Scale (Proposed Revision 8/9/93).



AUTHORIZED SIGNATURE
GOVMARK
/bg /jb

MS. PHYLLIS PETTIT

MAY 18 2015

(Page 2 of 2)



Received:04/01/2015 Completed:04/02/2015 Letter: R1 BG P.O.#: Test Report #: 3-07222-1-

Client's Identification

Style: Super Print Smooth Banner. Composition: Polyester. Product End Use: Banners.

Tested For: Kylie Schleicher

Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869

Key Test: CA 1237 Sm

175

Tel: 1-(973)-627-8608 **Ext:**
Fax: 1-()- -

PC: 1H /jd SM/mg

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - EXTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED: ☒ Initially
☐ After 72 hours water leaching
☐ After 100 hours weathering

RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)
Warp:	1	0	0	4.7
	2	0	0	4.7
	3	0	0	4.3
	4	0	0	5.1
	5	0	0	5.3
	Avg:	0		
Fill:	6	0	0	4.5
	7	0	0	5.3
	8	0	0	5.0
	9	0	0	4.7
	10	0	0	5.0
	Avg:	0		

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 10.2 oz/yd²

ACCEPTANCE CRITERIA:

Afterflame: 4.0 seconds maximum avg for length or width
Afterglow: (see Note #2 below)
Char Length: 6.0" maximum for any individual specimen

NOTES:

1. An asterisk (*) next to any char length measurements indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd².
2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.

Received: 04/01/2015	Completed: 04/02/2015	Letter: R1	BG	P.O.#:	Test Report #:	3-07222-1-
Client's Identification	Style: Super Print Smooth Banner. Composition: Polyester. Product End Use: Banners.					
Tested For: Kylie Schleicher Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869				Key Test: CA 1237 Sm		175
				Tel: 1-(973)-627-8608		Ext:
				Fax: 1-()- -		

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

☒ Complies; ☐ Does not comply

REMARKS: None.

NOTE: The number of test specimens and Acceptance Criteria are based on a proposed revision issued and implemented by the California State Fire Marshal in August 1993. In substance, the following has occurred:

1. A maximum afterflame of 4 seconds is permitted as opposed to 2 seconds.
2. It was clarified that the char length maximum of 6 inches applies to any individual specimen and is not an average requirement.
3. Ten specimens are tested in lieu of 6 specimens.

This report issues the conclusion to Section 1237 based on the California State Fire Marshal's continued endorsement of the proposed revision.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



MS. PHYLLIS PETTIT

AUTHORIZED SIGNATURE

GOVMARK

/pm

q6/

APR 03 2015

(Page 2 of 2)



96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Page 1

Received: 04/01/2015 Completed: 04/02/2015 Letter: R1 BG P.O.#: Test Report #: 3-07222-1-

Client's Identification Style: Super Print Smooth Banner. Composition: Polyester. Product End Use: Banners.

Tested For: **Kyle Schleicher** Key Test: CA 1237 Sm 175
Ultraflex Systems Inc.
1578 Sussex Tpk., Bldg. #4
Randolph, NJ 07869
Tel: 1-(973)-627-8608 Ext:
Fax: 1-()- -

PC: 1H /jd SM/mg

TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - EXTERIOR MATERIALS QUALIFICATION

RESULTS REPORTED: ☒ Initially
☐ After 72 hours water leaching
☐ After 100 hours weathering

RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)
Warp:	1	0	0	4.7
	2	0	0	4.7
	3	0	0	4.3
	4	0	0	5.1
	5	0	0	5.3
	Avg:	0		
Fill:	6	0	0	4.5
	7	0	0	5.3
	8	0	0	5.0
	9	0	0	4.7
	10	0	0	5.0
	Avg:	0		

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 10.2 oz/yd²

ACCEPTANCE CRITERIA:

Afterflame: 4.0 seconds maximum avg for length or width
Afterglow: (see Note #2 below)
Char Length: 6.0" maximum for any individual specimen

NOTES:

1. An asterisk (*) next to any char length measurements indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd².
2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.



Govmark

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Page 2

Received: 04/01/2015	Completed: 04/02/2015	Letter: R1	BG	P.O.#:	Test Report #:	3-07222-1-
Client's Identification	Style: Super Print Smooth Banner. Composition: Polyester. Product End Use: Banners.					
Tested For: Kylie Schleicher Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869			Key Test: CA 1237 Sm			175
			Tel: 1-(973)-627-8608			Ext:
			Fax: 1-()- -			

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

☒ Complies; ☐ Does not comply


REMARKS: None.

NOTE: The number of test specimens and Acceptance Criteria are based on a proposed revision issued and implemented by the California State Fire Marshal in August 1993. In substance, the following has occurred:

1. A maximum afterflame of 4 seconds is permitted as opposed to 2 seconds.
2. It was clarified that the char length maximum of 6 inches applies to any individual specimen and is not an average requirement.
3. Ten specimens are tested in lieu of 6 specimens.

This report issues the conclusion to Section 1237 based on the California State Fire Marshal's continued endorsement of the proposed revision.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.



AUTHORIZED SIGNATURE
GOVMARK

/pm

lgb

MS. PHYLLIS PETTIT

APR 03 2015

(Page 2 of 2)