

Bravura™ Display 450 is a 450 micron, non-curl, PP and PET film designed specifically for pop-up display systems. The material has a smooth print surface and a quick drying top coat and bright white point. Bravura Display 450 has a white backside that prevents translucency issues. Bravura Display 450 is solvent, eco-solvent, UV & Latex printable. Available in widths from 36" – 60" on 98' long rolls.

### Material Details

| CHARACTERISTICS | TEST METHOD | METRIC                 | ENGLISH                 |
|-----------------|-------------|------------------------|-------------------------|
| Base Material   |             |                        | PP & PET                |
| Total Weight    | ASTM D646   | 520±5 g/m <sup>2</sup> | 15.33oz/yd <sup>2</sup> |
| Total Thickness | ASTM D645   |                        | 450 micron              |
| Whiteness       | ASTM E313   |                        | 95                      |
| Opacity         | ISO 2471    |                        | > 99.99                 |
| Surface Finish  |             |                        | Semi-Matte              |

### Applications

|              | Back-lit Banners | Blockout | Exhibition Panels | Special Effects Displays | Transit Graphics | Display Systems | High Res. Posters |
|--------------|------------------|----------|-------------------|--------------------------|------------------|-----------------|-------------------|
| Applications |                  | ■        | ■                 | ■                        | ■                | ■               | ■                 |

### Ink Printability

| Solvent | Eco Solvent | UV | Latex | Screen Printing | Dye Transfer | Dye Direct |
|---------|-------------|----|-------|-----------------|--------------|------------|
| ■       | ■           | ■  | ■     |                 |              |            |

### Available Sizes

| Metric (m)        | English (inches) |
|-------------------|------------------|
| 0.914, 1.37, 1.52 | 36", 54", 60"    |

The information on physical and chemical characteristics is based upon tests believed to be reliable. The values are intended only as a source of information. A legally binding guarantee of specific properties is not to be inferred from our specifications. They are given without guaranty and do not constitute a warranty. The purchaser should independently determine, prior to use, the suitability of this material for his/her specific purpose. (Data represents averages and is not intended for use as a specification.)